

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 344 795 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
17.09.2003 Bulletin 2003/38

(51) Int Cl.7: **C08K 9/04**

(21) Application number: **03100546.5**

(22) Date of filing: **05.03.2003**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR**
Designated Extension States:
AL LT LV MK

(30) Priority: **13.03.2002 JP 2002068151**

(71) Applicant: **NISSHINBO INDUSTRIES, INC.**
Tokyo 103 (JP)

(72) Inventors:

- Ikuo, Takahashi Nisshinbo Ind. INC.
Midori-ku, Chiba-shi Chiba, Chiba (JP)
- Toshifumi, Hashiba Nisshinbo Ind. INC.
Midori-ku, Chiba-shi Chiba, Chiba (JP)
- Kazutoshi, Hayakawa Nisshinbo Ind. INC.
Midori-ku, Chiba-shi Chiba, Chiba (JP)

(74) Representative: **Moinas, Michel et al**
Cabinet Michel Moinas
13 Chemin du Levant
01210 Ferney-Voltaire (FR)

(54) **Carbodiimide-containing hardening type reactive particles, process for producing the same, and use of the same**

(57) A hardening type reactive particles which contain a carbodiimide compound in such a way to have the reactive performance the carbodiimide group inherently has only in the surface layer section or both surface layer section and inside of the base particle, without deforming shape of the base particle. The hardening type reactive particles each comprising a base particle (A) of thermoplastic resin having a functional group and carbodiimide compound (B) impregnated only in the sur-

face layer section or both surface layer section and inside of the base particle, wherein the base particle (A) and carbodiimide compound (B) are strong bonded to each other by the crosslinking reaction taking place under heating between the functional group in the former and carbodiimide group in the latter, and a process for producing the same.

Description

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

[0001] The present invention relates to carbodiimide-containing, hardening type reactive particles, process for producing the same and use of the same, more particularly hardening type reactive particles each comprising a base particle (A) of thermoplastic resin having a functional group and carbodiimide compound (B) impregnated only in the surface layer section or both surface layer section and inside of the base particle, and process for producing the same and use of the same.

DESCRIPTION OF THE PRIOR ART

[0002] Carbodiimide, having a structure of $-N=C=N-$, has been widely used as a stabilizer for improving hydrolysis resistance for compounds having an ester group or crosslinking agent for resins, e.g., (meth)acrylic resin, having carboxyl group reactive with carbodiimide group, where high reactivity of carbodiimide group is generally utilized.

[0003] Various applicable areas have been proposed for carbodiimide resins, e.g., paints, adhesives and coating agents, as disclosed by Japanese Patent Application Laid-Open Nos. 10-60272 and 10-30024, and they have been already commercialized in these areas.

[0004] However, most of the resins to be crosslinked with a carbodiimide-containing composition are in the form of solution of molten resin, paste or emulsion. Hardening of solid particles themselves requires a great deal of time and are hence difficult.

[0005] Production of polyolefin-based resin particles of crosslinked structure by the reaction with a carbodiimide compound in a melting/kneading machine or the like has been studied, as disclosed by, e.g., Japanese Patent Application Laid-Open No.2000-155441. However, the particles which can sufficiently satisfy resistance to heat and chemicals have not been developed.

[0006] Broadly speaking, the processes for producing polymer particles fall into two general categories; (I) production of the objective particles by crushing and classifying the resin produced by, e.g., block or solution polymerization, as known, and (II) production of adequate particles during a polymerization stage, e.g., suspension, emulsion or dispersion polymerization, or seed process based on these processes.

[0007] When hardened particles are to be produced, most of these approaches incorporate a crosslinkable vinyl-based monomer or polymer to improve resistance to heat and chemicals, or incorporate a crosslinkable monomer or polymer other than a vinyl-based one, e.g., epoxy resin or the like, to improve resistance to heat and solvents.

SUMMARY OF THE INVENTION

[0008] It is an object of the present invention to provide hardening type reactive particles each comprising a base particle of thermoplastic resin which contains a carbodiimide compound in such a way to have the reactive performance the carbodiimide group inherently has only in the surface layer section or both surface layer section and inside of the base particle, without deforming shape of the base particle.

[0009] The inventors of the present invention have found, after having extensively studied to solve the problems involved in the conventional techniques, that a thermoplastic resin particle having a group reactive with carbodiimide group (e.g., hydroxyl, amino, carboxyl or thiol group), when mixed and crosslinked with a carbodiimide resin under heating in the presence of water or an organic solvent which dissolves the carbodiimide resin but not the particle, comes to show resistance both to heat and solvent, and to be a functional reactive particle with at least one carbodiimide group in the surface or both inside and in the surface. The present invention is developed based on the above knowledge.

[0010] The first aspect of the present invention provides hardening type reactive particles each comprising a base particle (A) of thermoplastic resin having a functional group and carbodiimide compound (B) impregnated only in the surface layer section or both surface layer section and inside of the base particle, wherein the base particle (A) and carbodiimide compound (B) are strong bonded to each other by the crosslinking reaction taking place under heating between the functional group in the former and carbodiimide group in the latter.

[0011] The second aspect of the present invention provides the hardening type reactive particles of the first aspect, wherein the base particle (A) has an average diameter of 0.01 to 10,000 μ m.

[0012] The third aspect of the present invention provides the hardening type reactive particles of the first aspect, wherein the base particle (A) is morphologically truly or nearly spherical.

[0013] The fourth aspect of the present invention provides the hardening type reactive particles of the first aspect,

wherein the functional group is at least one type of active hydrogen group selected from the group consisting of hydroxyl, carboxyl, amino and thiol group.

[0014] The fifth aspect of the present invention provides the hardening type reactive particles of the first aspect, wherein the thermoplastic resin has 30 to 700 equivalents of the functional groups.

[0015] The sixth aspect of the present invention provides the hardening type reactive particles of the first aspect, wherein the thermoplastic resin is one of styrene-based polymer, (meth)acrylate-based polymer, a copolymer produced by addition polymerization with another vinyl-based polymer, polymer produced by hydrogen transfer polymerization, polymer produced by polycondensation or polymer produced by addition condensation.

[0016] The seventh aspect of the present invention provides the hardening type reactive particles of the first aspect, wherein the carbodiimide compound (B) is the carbodiimide resin represented by the chemical formula (1):



(wherein, R¹ and R³ are each hydrogen or an organic residue of 1 to 40 carbon atoms, which is a compound having a functional group reactive with isocyanate group left by the functional group, and may be the same or different; R² is an organic residue which is a diisocyanate left by isocyanate group, where the diisocyanates may be different; Y is a bond formed by isocyanate group and a functional group reactive with isocyanate group; "n" is an integer of 1 to 100, representing average degree of polymerization; and each of R¹-Y and Y-R³ may be isocyanate group halfway in the reaction to be converted into the carbodiimide).

[0017] The eighth aspect of the present invention provides the hardening type reactive particles of the seventh aspect, wherein the carbodiimide resin has 50 to 500 equivalents of the carbodiimide (-NCN-) groups.

[0018] The ninth aspect of the present invention provides the hardening type reactive particles of the seventh aspect, wherein the carbodiimide resin has an average molecular weight of 200 to 100,000.

[0019] The tenth aspect of the present invention provides the hardening type reactive particles of the seventh aspect, wherein the carbodiimide resin has at least one type of hydrophilic segment and is soluble in water.


[0020] The 11th aspect of the present invention provides the hardening type reactive particles of the tenth aspect, wherein the hydrophilic segment is represented by the chemical formula (1) with R¹ and R³ being each at least one type of residue represented by one of the chemical formulae (2) to (5):

(i) a residue of alkyl sulfonate having at least one reactive hydroxyl group, represented by:



(wherein, R⁴ is an alkylene group of 1 to 10 carbon atoms; and R⁵ is an alkali metal),

(ii) a quaternary salt of a dialkylaminoalcohol residue represented by:



(wherein, R⁶ is a lower alkyl group of 1 to 4 carbon atoms; R⁷ is an alkylene or oxyalkylene group of 1 to 10 carbon atoms; and R' is a group derived from an agent for producing a quaternary salt),

(iii) a quaternary salt of a dialkylaminoalkylamine residue represented by:



(wherein, R⁶, R⁷ and R' are each the same as the corresponding one in the formula (3)); and

(iv) a poly(alkylene oxide) residue sealed with alkoxy group at the terminals, having at least one reactive hydroxyl group, represented by:



(wherein, R⁸ is a lower alkyl group of 1 to 4 carbon atoms; R⁹ is hydrogen atom or methyl group; and "m" is an integer of 2 to 30).

[0021] The 12th aspect of the present invention provides a process for producing the hardening type reactive particles of one of first to 11th aspects comprising two steps: the first step in which the base particle (A) of thermoplastic resin having a functional group is mixed with the carbodiimide compound (B) in the presence of at least one type of solvent which dissolves (B) but not (A), selected from the group consisting of water and organic compounds, to have the latter impregnated only in the surface layer section or both surface layer section and inside of the former; and the subsequent second step in which the above mixture is thermally treated.

[0022] The 13th aspect of the present invention provides the process of the 12th aspect, wherein the base particle (A) is morphologically truly or nearly spherical.

[0023] The 14th aspect of the present invention provides the process of the 13th aspect, wherein the base particle (A) is the one prepared beforehand by suspension, emulsion, dispersion or seed polymerization.

[0024] The 15th aspect of the present invention provides the process of the 12th aspect, wherein the base particle (A) is immersed in a solution of the carbodiimide compound (B) dissolved in at least one type of solvent selected from the group consisting of water and organic solvents in said first step.

[0025] The 16th aspect of the present invention provides the process of the 15th aspect, wherein concentration of the carbodiimide compound (B) in the solution is 5 to 60% by weight, determined by the following formula:

$$\text{Solution concentration (\% by weight)} = 100 \times (\text{whole solution-solvent})/\text{whole solution}.$$

[0026] The 17th aspect of the present invention provides the process of the 12th aspect, wherein the solvent is water, a mixture of water and a lower alcohol, or toluene.

[0027] The 18th aspect of the present invention provides the process of the 12th aspect, wherein the base particle (A) is mixed with the carbodiimide compound in a ratio of 0.1 to 20 equivalents of the carbodiimide group in the carbodiimide compound (B) to equivalent of the functional group in the base particle (A).

[0028] The 19th aspect of the present invention provides the process of the 12th aspect, wherein the thermal treatment in the second step is effected at 10 to 200°C.

[0029] The 20th aspect of the present invention provides the process of the 12th aspect, wherein the thermal treatment in the second step is effected for 1 to 24 hours.

[0030] The 21st aspect of the present invention provides the process of the 12th aspect, wherein the functional group is at least one type of active hydrogen group selected from the group consisting of hydroxyl, carboxyl, amino and thiol group.

[0031] The 22nd aspect of the present invention provides the process of the 21st aspect, wherein the thermoplastic resin is one of styrene-based polymer, (meth)acrylate-based polymer, a copolymer produced by addition polymerization with another vinyl-based polymer, polymer produced by hydrogen transfer polymerization, polymer produced by polycondensation or polymer produced by addition condensation.

[0032] The 23rd aspect of the present invention provides the process of the 12th aspect, wherein the carbodiimide compound (B) has an average molecular weight of 200 to 100,000.

[0033] The 24th aspect of the present invention provides the process of the 12th aspect, wherein the carbodiimide compound (B) has at least one type of hydrophilic segment and is soluble in water.

[0034] The 25th aspect of the present invention provides the process of the 24th aspect, wherein the hydrophilic segment is represented by the chemical formula (1) with R¹ and R³ being each at least one type of residue represented by one of the chemical formulae (2) to (5).

[0035] The 26th aspect of the present invention provides the process of the 12th aspect, wherein at least one type of additive selected from the group consisting of dispersant, antioxidant, stabilizer and emulsifier is added to the first step, in addition to the base particle (A) and carbodiimide compound (B).

[0036] The 27th to 32nd aspects of the present invention provide a crosslinking agent, stabilizer for improving hydrolysis resistance, thermoplastic resin-hardening agent, adhesive agent, coating material or paint, and reinforcing material for the electric/electronic areas, respectively, which comprise the hardening type reactive particles according to one of Claims 1 to 11.

[0037] As described above, the present invention relates to hardening type reactive particles each comprising a base particle (A) of thermoplastic resin having a functional group and carbodiimide compound (B) impregnated only in the surface layer section or both surface layer section and inside of the base particle, wherein the base particle (A) and carbodiimide compound (B) are strong bonded to each other by the crosslinking reaction taking place under heating between the functional group in the former and carbodiimide group in the latter, a process for producing the same, and use of the same. The preferred embodiments include the followings:

(1) The hardening type reactive particles of the first aspect of the present invention, wherein the particles are semi-hardened.

(2) The hardening type reactive particles of the first aspect of the present invention, wherein the base particle (A) is non-spherical.

(3) The process for producing the hardening type reactive particles of (2), wherein the base particle (A) is produced by block polymerization, solution polymerization or dropping method.

(4) The process of the 12th aspect of the present invention for producing the hardening type reactive particles, wherein the solvent is selected from the group consisting of dimethylformamide (DMF), tetrahydrofuran (THF), methylethylketone (MEK), methylisobutylketone (MIBK), acetone, N-methyl-2-pyrrolidone (NMP), dichloromethane and tetrachloroethylene.


DETAILED DESCRIPTION OF THE INVENTION

[0038] The present invention is described below in detail for each item.

1. Hardening type reactive particles

[0039] Each of the hardening type reactive particles of the present invention comprises a base particle (A) of thermoplastic resin having a functional group and carbodiimide compound (B) impregnated only in the surface layer section or both surface layer section and inside of the base particle, wherein the base particle (A) and carbodiimide compound (B) are strong bonded to each other by the crosslinking reaction taking place under heating between the functional group in the former and carbodiimide group in the latter.

[0040] The hardening type reactive particle has a chemical structure, conceptually illustrated below:



[0041] In the above chemical formula, "n" is random, and some (at least one) of the carbodiimide groups in the polycarbodiimide molecule are bonded to the particle inside or surface (surface layer section). The one whose terminal R is a reactive group, e.g., isocyanate, is reactive with a terminal group.

[0042] Moreover, the carbodiimide group can be preferentially bonded to the thermoplastic resin particle surface (surface layer section) or crosslinked only on the particle surface (surface layer section), as required, by selecting the carbodiimide resin type.

[0043] The hardening type reactive particles may be hardened or semi-hardened.

2. Carbodiimide compound (B)

[0044] The carbodiimide compound (B) for the hardening type reactive particles of the present invention is the carbodiimide resin (or polycarbodiimide) represented by the chemical formula (1):




(wherein, R^1 and R^3 are each hydrogen or an organic residue of 1 to 40 carbon atoms, which is a compound having a functional group reactive with isocyanate group left by the functional group, and may be the same or different; R^2 is an organic residue which is a diisocyanate left by isocyanate group, where the diisocyanates may be different; Y is a

bond formed by isocyanate group and a functional group reactive with isocyanate group; "n" is an integer of 1 to 100, representing average degree of polymerization; and each of R^1 -Y and Y- R^3 may be isocyanate group halfway in the reaction to be converted into the carbodiimide).

[0045] In more detail, R^1 or R^3 in the general formula (1) is at least one type of segment composed of a residue represented by a compound having a functional group or bond reactive with isocyanate group.

[0046] The representative examples of the functional group or bond include:

- (a) hydroxide group -OH (including H_2O)
- (b) mercapto group -SH
- (c) amino group $-NH_2$
- (d) carboxyl group $-COOH$
- (e) isocyanate group $-NCO$
- (f) urethane bond $-NHCOO-$
- (g) urea bond $-NHCONH-$
- (h) amide bond $-NHCO-$
- (i) carbodiimide bond $-NCN-$
- (j) dimerized isocyanate bond



[0047] More specifically, the representative compounds reactive with isocyanate group include:

(a) compounds containing hydroxyl group (-OH): (i) monovalent alcohols, e.g., methyl alcohol, ethyl alcohol, propyl alcohol, isopropyl alcohol, n-butyl alcohol, sec-butyl alcohol and tert-butyl alcohol; (ii) saturated or unsaturated glycols, e.g., ethylene glycol, propylene glycol, trimethylol propane, pentaerythritol, 1,2-propanediol, 1,3-propanediol, 1,3-butanediol, 1,4-butanediol, neopentyl glycol, pentanediol, hexanediol, octanediol, 1,4-butanediol, diethylene glycol, triethylene glycol and dipropylene glycol; (iii) cellosolve; e.g., methyl cellosolve, ethyl cellosolve and butyl cellosolve; (iv) (meth)acrylate-based monomers, e.g., 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, 3-hydroxypropyl (meth)acrylate and 4-hydroxybutyl (meth)acrylate; (v) polyalkylene glycol (meth)acrylate-based compounds, e.g., polyethylene glycol mono(meth)acrylate and polypropylene glycol mono(meth)acrylate; (vi) various types of hydroxyalkyl vinyl ethers, e.g., hydroxyethyl vinyl ether and hydroxybutyl vinyl ether; (vii) various allyl compounds, e.g., allyl alcohol and 2-hydroxyethyl allyl ether; (viii) alkyl glycidyl ethers, e.g., n-butyl glycidyl ether and 2-ethylhexyl glycidyl ether; and (ix) high-molecular-weight compounds containing hydroxyl group, e.g., polyethylene glycol and polypropylene glycol (these compounds may be used either individually or in combination);

(b) compounds containing mercapto group: (i) aliphatic alkyl mono-functional thiols, e.g., methanethiol, ethanethiol, n- and iso-propanethiol, n- and iso-butanethiol, pentanethiol, hexanethiol, heptanethiol, octanethiol, nonanethiol, decanethiol and cyclohexanethiol; (ii) aliphatic thiols having a heterocyclic ring, e.g., 1,4-dithian-2-thiol, 2- (1-mercaptomethyl) - 1,4-dithian, 2- (1-mercaptoethyl) - 1,4-dithian, 2- (1-mercaptopropyl) - 1,4-dithian, 2- (mercaptobutyl) - 1,4-dithian, tetrahydrothiophene-2-thiol, tetrahydrothiophene-3-thiol, pyrrolidine-2-thiol, pyrrolidine-3-thiol, tetrahydrofuran-2-thiol, tetrahydrofuran-3-thiol, piperidine-2-thiol, piperidine-3-thiol and piperidine-4-thiol; (iii) aliphatic thiols having a hydroxy group, e.g., 2-mercaptoethanol, 3-mercaptopropanol and thioglycerol; (iv) compounds having a double bond, e.g., 2-mercaptoethyl (meth)acrylate, 2-mercapto-1-carboxyethyl (meth)acrylate, N-(2-mercaptoethyl)acrylamide, N-(2-mercapto-1-carboxyethyl)acrylamide, N-(2-mercaptoethyl)methacrylamide, N-(4-mercaptophenyl)acrylamide, N-(7-mercaptonaphthyl)acrylamide and mono-2-mercaptoethylamide maleate; (v) aliphatic dithiols, e.g., 1,2-ethanedithiol, 1,3-propanedithiol, 1,4-butanedithiol, 1,6-hexanedithiol, 1,8-octanedithiol, 1,2-cyclohexanedithiol, ethylene glycol bithioglycolate, ethylene glycol bithiopropionate, butanediol bithioglycolate, butanediol bithiopropionate, trimethylolpropane trithioglycolate, trimethylolpropane trithiopropionate, pentaerythritol tetrakisthioglycolate, pentaerythritol tetrakisthiopropionate, tris(2-mercaptoethyl)isocyanurate and tris(3-mercaptopropyl)isocyanurate; (vi) aromatic dithiols, e.g., 1,2-benzenedithiol, 1,4-benzenedithiol,

4-methyl-1,2-benzenediol, 4-butyl-1,2-benzenediol and 4-chloro-1,2-benzenediol; and (vii) high-molecular-weight compounds containing mercapto group, e.g., modified polyvinyl alcohol containing mercapto group (these compounds may be used either individually or in combination);

(c) compounds containing amino group: (i) aliphatic or aromatic amine-containing compounds, e.g., ammonia, methylamine, ethylamine, n-propylamine, isopropylamine, monoethanolamine, n-propanolamine, isopropanolamine, aniline, cyclohexylamine, n-butylamine, n-pentylamine, n-hexylamine, n-heptylamine, n-octylamine, n-nonylamine, n-decylamine, n-undecylamine, n-dodecylamine, n-tridecylamine, n-tetradecylamine, n-pentadecylamine, n-hexadecylamine, n-heptadecylamine, n-octadecylamine, n-eicosylamine, aminomethyltrimethylsilane, aminomethyltriethylsilane, aminomethyltripropylsilane, aminoethyltrimethylsilane, aminoethyltriethylsilane, aminoethyltripropylsilane, aminopropyltrimethylsilane, aminopropyltriethylsilane, aminopropyltripropylsilane, aminomethyltrimethoxysilane, aminomethyltriethoxysilane, aminomethyltripropoxysilane, aminomethyldimethoxymethylsilane, aminomethylmethoxydimethylsilane, aminomethyldiethoxymethylsilane, aminomethylethoxydimethylsilane, aminomethylmethoxyethylsilane, aminomethylmethoxydiethylsilane, aminomethyldiethoxyethylsilane, aminomethylethoxydiethylsilane, aminoethyldimethoxymethylsilane, aminoethylmethoxydimethylsilane, aminoethyldiethoxymethylsilane, aminoethylethoxydimethylsilane, aminoethyldimethoxyethylsilane, aminoethylethoxydiethylsilane, aminopropyldimethoxymethylsilane, aminopropylmethoxydimethylsilane, aminopropyldiethoxymethylsilane, aminopropylethoxydimethylsilane, aminopropyldimethoxyethylsilane, aminopropylmethoxydiethylsilane, aminopropyldiethoxyethylsilane, aminopropylethoxydiethylsilane, aminomethylphenyldimethylsilane, diethylamine, diethanolamine, di-n-propanolamine, di-isopropanolamine, N-methylethanolamine and N-ethylethanolamine; (ii) alkylamino acrylates, e.g., dimethylaminoethyl acrylate, diethylaminoethyl acrylate, dimethylaminomethyl acrylate, diethylaminomethyl acrylate, adduct of diacrylate and diethylamine, and adduct of trimethylolpropane triacrylate and diethylamine; (iii) alkylaminoalkylvinyl ethers, e.g., (meth)acrylamide, α -ethyl (meth)acrylamide, N-methyl (meth)acrylamide, N-butoxymethyl (meth)acrylamide, diacetone (meth)acrylamide, N,N-dimethyl (meth)acrylamide, N,N-diethyl (meth)acrylamide, N,N-dimethyl-p-styrenesulfoamide, N,N-dimethylaminoethyl (meth)acrylate, N,N-diethylaminoethyl (meth)acrylate, N,N-dimethylaminopropyl (meth)acrylate, N,N-diethylaminopropyl (meth)acrylate, N-[2-(meth)acryloyloxyethyl]piperidine, N-[2-(meth)acryloyloxyethyl]pyrrolidine, N-[2-(meth)acryloyloxyethyl]morpholine, 4-(N,N-dimethylamino)styrene, 4-(N,N-diethylamino)styrene, 4-vinyl pyridine, 2-dimethylaminoethylvinyl ether, 2-diethylaminoethylvinyl ether, 4-dimethylaminobutylvinyl ether, 4-diethylaminobutylvinyl ether and 6-dimethylaminohexylvinyl ether; and (iv) high-molecular-weight compounds containing amino group (these compounds may be used either individually or in combination);

(d) compounds containing carboxyl group: (i) saturated aliphatic monocarboxylates, e.g., formic, acetic, propionic, isovaleric and hexanoic acid; (ii) saturated aliphatic dicarboxylates, e.g., oxalic, malonic and succinic acid; (iii) organic carboxylic acids, e.g., 2-acryloyloxyethylsuccinic and 3-acryloyloxypropylphthalic acid; (iv) carbocyclic carboxylic acids, e.g., benzoic, toluyl and salicylic acid; (v) heterocyclic carboxylic acids, e.g., furancarboxylic, thiophenecarboxylic and pyridinecarboxylic acid; (vi) various unsaturated mono- or di-carboxylic or unsaturated dibasic acids, e.g., acrylic, methacrylic, crotonic, itaconic, maleic and fumaric acid, and monobutyl itaconate and monobutyl maleate; (vii) acid anhydrides derived from carboxylic acid, e.g., acetic, succinic and phthalic anhydride; and (viii) high-molecular-weight carboxylic acids, e.g., polyacrylic and polymethacrylic acid (these compounds may be used either individually or in combination);

(e) compounds containing isocyanate group: (i) cyclohexyl isocyanate, n-decyl isocyanate, n-undecyl isocyanate, n-dodecyl isocyanate, n-tridecyl isocyanate, n-tetradecyl isocyanate, n-pentadecyl isocyanate, n-hexadecyl isocyanate, n-heptadecyl isocyanate, n-octadecyl isocyanate, n-eicosyl isocyanate, phenyl isocyanate and naphthyl isocyanate; and (ii) isocyanate compounds having 2 or more isocyanate groups, e.g., those used for carbodiimide resins (these compounds may be used either individually or in combination); and

(f) to (j): compounds having a representative bonding group reactive with an isocyanate group, which can be produced by polymerization of the compound of (a) to (e), respectively, with a varying isocyanate compound under heating in the presence or absence of catalyst.

[0048] The representative compounds reactive with isocyanate group are not limited to those compounds (a) to (j). Any compound may be used, so long as it has a functional group or bond reactive with isocyanate group (e.g., acid anhydride and compound having a double bond). They may be used either individually or in combination.

[0049] When R¹ or R³ in the chemical formula (1) is a residue represented by the compound of one of (a) to (j) having the functional group or bond, the bond Y is represented by:

(a') urethane bond -NHCOO-


(b') thiourethane bond -NHCSO-

(c') urea bond -NHCONH-


(d') amide bond -NHCO-

(e') carbodiimide bond -NCN-


(in the presence of a catalyst) or dimerized isocyanate bond




(f') allophanate




(g') burrette bond




(h') acylurea bond



(i') uretonimine bond



(j') trimerized isocyanate bond



[0050] The carbodiimide resin represented by the chemical formula (1) has an average molecular weight of 200 to

100,000, preferably 500 to 50,000.

[0051] The isocyanates as the starting compounds for producing the carbodiimide compound for the present invention include those having per molecule at least 2 isocyanate groups, preferably one or more isocyanates selected from bifunctional isocyanate, hexamethylene diisocyanate (hereinafter sometimes referred to as HDI), hydrogenated xylylene diisocyanate (H_6XDI), xylylene diisocyanate (XDI), 2,2,4-trimethylhexamethylene diisocyanate ($TMHDI$), 1,12-diisocyanatedodecane (DDI), norbornane diisocyanate ($NBDI$), 4,4'-dicyclohexylmethane diisocyanate ($HMDI$) and tetramethylxylylene diisocyanate ($TMXDI$), isophorone diisocyanate ($IPDI$), 2,4,6-triisopropylphenyl diisocyanate ($TIDI$), 4,4'-diphenylmethane diisocyanate (MDI), tolylene diisocyanate (TDI) and hydrogenated tolylene diisocyanate ($HTDI$), among others.

[0052] The first step for producing the carbodiimide compound for the present invention is heating the above-described isocyanate in the presence of a carbodiimidation catalyst.

[0053] The catalyst useful for the present invention is not limited, so long as it can accelerate the carbodiimidation reaction, but organophosphorus-based compounds are suitable, in particular phospholene oxides for their activity.

[0054] More specifically, these phospholene oxides include 3-methyl-1-phenyl-2-phospholene-1-oxide, 3-methyl-1-ethyl-2-phospholene-1-oxide, 1,3-dimethyl-2-phospholene-1-oxide, 1-phenyl-2-phospholene-1-oxide, 1-ethyl-2-phospholene-1-oxide, 1-methyl-2-phospholene-1-oxide and a double-bond isomer thereof, of which 3-methyl-1-phenyl-2-phospholene-1-oxide is more suitable for its industrial availability. Timing of incorporation of the carbodiimidation catalyst is not limited, i.e., it may be incorporated before, during or after the isocyanate is heated. It is however preferable to incorporate the catalyst while the reaction system is at a relatively low temperature for safety considerations.

[0055] The first step for producing the carbodiimide compound for the present invention is heating the above-described isocyanate in the presence of a carbodiimidation catalyst, as described above. The synthesis process may be effected in the presence or absence of a solvent, or a solvent may be added while the reaction process is proceeding. Whether a solvent is used or not, or its addition timing, when used, can be selected depending on specific purposes or objects of the carbodiimide compound.

[0056] The specific examples of the solvents useful for the present invention include ketones, e.g., acetone, methyl ethyl ketone, methyl isobutyl ketone and cyclohexanone; esters, e.g., ethyl acetate, butyl acetate, ethyl propionate and cellosolve acetate; aliphatic or aromatic hydrocarbons, e.g., pentane, 2-methylbutane, n-hexane, cyclohexane, 2-methylpentane, 2,2-dimethylbutane, 2,3-dimethylbutane, heptane, n-octane, isooctane, 2,2,3-trimethylpentane, decane, nonane, cyclopentane, methylcyclopentane, methylcyclohexane, ethylcyclohexane, p-menthane, benzene, toluene, xylene and ethylbenzene; halogenated hydrocarbons, e.g., carbon tetrachloride, trichloroethylene, chlorobenzene and tetrabromoethane; ethers, e.g., ethyl ether, dimethyl ether, trioxane and tetrahydrofuran; acetals, e.g., methylal and diethyl acetal; and sulfur- or nitrogen containing organic compounds, e.g., nitropropene, nitrobenzene, pyridine, dimethylformamide and dimethylsulfoxide. The solvent is not limited, so long as it is not harmful to the isocyanate or carbodiimide group during the synthesis process, and can be selected, as required, for a specific purpose of the polymerization process. These solvents may be used either individually or in combination.

[0057] The following compounds may be used as diluents, in addition to the above solvents, provided that the carbodiimide resin terminal is sealed with the hydrophilic segment, described later, after completion of the synthesis process: water; alcohols, e.g., methanol, ethanol, 1-propanol, 2-propanol, 1-butanol, 2-butanol, isobutyl alcohol, tert-butyl alcohol, 1-pentanol, 2-pentanol, 3-pentanol, 2-methyl-1-butanol, isopentyl alcohol, tert-pentyl alcohol, 1-hexanol, 2-methyl-1-pentanol, 4-methyl-2-pentanol, 2-ethyl butanol, 1-heptanol, 2-heptanol, 3-heptanol, 2-octanol, 2-ethyl-1-hexanol, benzyl alcohol and cyclohexanol; and ether alcohols, e.g., methyl cellosolve, ethyl cellosolve, isopropyl cellosolve, butyl cellosolve and diethylene glycol monobutyl ether. These may be used either individually or in combination. When used as a diluent, the above compound is preferably used at a relatively low temperature, because of high reactivity of the carbodiimide group.

[0058] A water-soluble polycarbodiimide is preferably used as the carbodiimide compound for the present invention, on account of recent environmental considerations.

[0059] Such a polycarbodiimide has a hydrophilic segment which is represented by, e.g., the chemical formula (1) with R^1 or R^3 being at least one type of residue represented by one of the chemical formulae (2) to (5).

(i) A residue of alkyl sulfonate having at least one reactive hydroxyl group, represented by:



(wherein, R^4 is an alkylene group of 1 to 10 carbon atoms; and R^5 is an alkali metal).

The alkyl sulfonates include sodium hydroxyethanesulfonate and sodium hydroxypropanesulfonate, of which the latter is more preferable.

(ii) A quaternary salt of a dialkylaminoalcohol residue represented by:



(wherein, R^6 is a lower alkyl group of 1 to 4 carbon atoms; R^7 is an alkylene or oxyalkylene group of 1 to 10 carbon atoms; and R' is a group derived from an agent for producing a quaternary salt).

The dialkylaminoalcohols include 2-dimethylaminoethanol, 2-diethylaminoethanol, 3-dimethylamino-1-propanol, 3-diethylamino-1-propanol, 3-diethylamino-2-propanol, 5-diethylamino-2-propanol and 2-(di-n-butylamino)ethanol, of which 2-dimethylaminoethanol is more preferable.

The agents for producing a quaternary salt include dimethylsulfuric acid and methyl p-toluenesulfonate.

(iii) A quaternary salt of a dialkylaminoalkylamine residue represented by:



(wherein, R^6 , R^7 and R' are each the same as the corresponding one in the formula (3)).

The dialkylaminoalkylamines include 3-dimethylamino-n-propylamine, 3-diethylamino-n-propylamine and 2-(diethylamino)ethylamine, of which 3-dimethylamino-n-propylamine is more preferable.

The agents for producing a quaternary salt include dimethylsulfuric acid and methyl p-toluenesulfonate.

(iv) A poly(alkylene oxide) residue sealed with alkoxy group at the terminals, having at least one reactive hydroxyl group, represented by:



(wherein, R^8 is a lower alkyl group of 1 to 4 carbon atoms; R^9 is hydrogen atom or methyl group; and "m" is an integer of 2 to 30).

The poly(alkylene oxides) include poly(ethylene oxide)monomethyl ether, poly(ethylene oxide)monoethyl ether, poly(ethylene oxide/propylene oxide)monomethyl ether and poly(ethylene oxide/propylene oxide)monoethyl ether, of which poly(ethylene oxide)monomethyl ether is more preferable.

3. Base particle (A) of thermoplastic resin and method for producing the same

[0060] The processes for producing the base particle (A) of thermoplastic resin having a functional group for the present invention include those for producing a thermoplastic resin having a functional group reactive with carbodiimide group (e.g., hydroxyl, carboxyl, amino or thiol group) and particles thereof. More specifically, they include:

(1) A process for producing the solution thermoplastic resin by common block or solution polymerization, and particles thereof by crushing and classifying the resin.

(2) A process for producing the thermoplastic resin by the above polymerization process, and particles (including spherical particles) thereof by dropping the polymer.

(3) A process for producing the thermoplastic resin and particles (including spherical particles) thereof by emulsion or suspension polymerization effected in an aqueous solution.

(4) A process for producing the thermoplastic resin and particles (including spherical particles) thereof by the above process (3) combined with a seed process or the like.

(5) A process for producing the thermoplastic resin and particles (mainly spherical particles) thereof by dispersion polymerization in a non-aqueous solvent or water-mixed solvent.

(6) A process for producing the thermoplastic resin and particles thereof by the above process (5) combined with a seed process or the like.

(7) Extrusion or the like to produce pellets, particles or film-shaped articles of the thermoplastic resin.

(8) Injection molding or the like to produce formed articles of the thermoplastic resin.

The processes for the present invention are not limited to the above, and any process may be used so long as it produces the composition and particles thereof which satisfy the necessary conditions, e.g., quantity of the functional

group in the thermoplastic resin and particles thereof, particle size, and thickness of the formed article.

[0061] In the process for producing the base particle (A) of thermoplastic resin, the particles produced by one of the above polymerization processes may have a crosslinked structure beforehand, and can be used for producing the hardening type reactive particles of the present invention.

[0062] The base particle (A) of thermoplastic resin for the present invention is the one having a functional group reactive with carbodiimide group. More specifically, it has an active hydrogen group, e.g., hydroxyl (-OH), carboxyl (-COOH), amino (-NH₂) or thiol (-SH) group.

[0063] The base particle of thermoplastic resin has a weight-average molecular weight of around 1,000 to 3,000,000, or 3,000 to 500,000 when it is spherical.

[0064] The thermoplastic resin is one of styrene-based polymer, (meth)acrylate-based polymer, a copolymer produced by addition polymerization with another vinyl-based polymer, polymer produced by hydrogen transfer polymerization, polymer produced by polycondensation and polymer produced by addition condensation.

[0065] The specific examples of the representative starting copolymerizable monomers as the main component for the above polymer include (i) styrenes, e.g., styrene, o-methyl styrene, m-methyl styrene, p-methyl styrene, α -methyl styrene, p-ethyl styrene, 2,4-dimethyl styrene, p-n-butyl styrene, p-tert-butyl styrene, p-n-hexyl styrene, p-n-octyl styrene, p-n-nonyl styrene, p-n-decyl styrene, p-n-dodecyl styrene, p-methoxystyrene, p-phenyl styrene, p-chlorostyrene and 3,4-dichlorostyrene; (ii) (meth)acrylate esters, e.g., methyl acrylate, ethyl acrylate, n-butyl acrylate, isobutyl acrylate, propyl acrylate, hexyl acrylate, 2-ethylhexyl acrylate, n-octyl acrylate, dodecyl acrylate, lauryl acrylate, stearyl acrylate, 2-chloroethyl acrylate, phenyl acrylate, methyl α -chloroacrylate, methyl methacrylate, ethyl methacrylate, n-butyl methacrylate, isobutyl methacrylate, propyl methacrylate, hexyl methacrylate, 2-ethylhexyl methacrylate, n-octyl methacrylate, dodecyl methacrylate, lauryl methacrylate and stearyl methacrylate; (iii) vinyl esters, e.g., vinyl acetate, vinyl propionate, vinyl benzoate and vinyl butyrate; (iv) (meth)acrylic acid derivatives, e.g., acrylonitrile and methacrylonitrile; (v) vinyl ethers, e.g., vinyl methyl ether, vinyl ethyl ether and vinyl isobutyl ether; (vi) vinyl ketones, e.g., vinyl methylketone, vinyl hexylketone and methylisopropenylketone; (vii) N-vinyl compounds, e.g., N-vinyl pyrrole, N-vinyl carbazole, N-vinyl indole and N-vinyl pyrrolidone; and (viii) (meth)acrylate esters having a fluorine-containing alkyl group, e.g., vinyl fluoride, vinylidene fluoride, tetrafluoroethylene, hexafluoropropylene, trifluoroethyl acrylate and tetrafluoropropyl acrylate. These compounds may be used either individually or in combination.

[0066] The specific examples of the representative radical-polymerizable monomers having carboxyl group as the functional group reactive with carbodiimide group include various unsaturated mono- and di-carboxylic acids and unsaturated dibasic acids, e.g., acrylic, methacrylic, crotonic, itaconic, maleic and fumaric acid, and monobutyl itaconate and monobutyl maleate. These compounds may be used either individually or in combination.

[0067] The specific examples of the representative radical-polymerizable monomers having hydroxyl group as the functional group reactive with carbodiimide group include (meth)acrylate-based monomers, e.g., 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, 3-hydroxypropyl (meth)acrylate and 4-hydroxybutyl (meth)acrylate; polyalkylene glycol (meth)acrylate-based compounds, e.g., polyethylene glycol mono(meth)acrylate and polypropylene glycol mono(meth)acrylate; various types of hydroxyalkyl vinyl ethers, e.g., hydroxyethyl vinyl ether and hydroxybutyl vinyl ether; and various allyl compounds, e.g., allyl alcohol and 2-hydroxyethyl allyl ether. These compounds may be used either individually or in combination.

[0068] The specific examples of the representative polymers having hydroxyl group include thermoplastic resins having hydroxyl group, e.g., totally or partially saponified resins (e.g., polyvinyl alcohol (PVA)), and saponified resins (e.g., acetate esters composed of a copolymer of vinyl acetate and another vinyl monomer). These polymers are also useful for the present invention.

[0069] The specific examples of the representative radical-polymerizable monomers or compounds having amino group as the functional group reactive with carbodiimide group include (meth)acrylamide, α -ethyl (meth)acrylamide, N-methyl (meth)acrylamide, N-butoxymethyl (meth)acrylamide, diacetone (meth)acrylamide, N,N-dimethyl (meth)acrylamide, N,N-diethyl (meth)acrylamide, N,N-dimethyl-p-styrenesulfoamide, N,N-dimethylaminoethyl (meth)acrylate, N,N-diethylaminoethyl (meth)acrylate, N,N-dimethylaminopropyl (meth)acrylate, N,N-diethylaminopropyl (meth)acrylate, N-[2-(meth)acryloyloxyethyl]piperidine, N-[2-(meth)acryloyloxyethylene]pyrrolidine, N-[2-(meth)acryloyloxyethyl]morpholine, 4-(N,N-dimethylamino)styrene, 4-(N,N-diethylamino)styrene, 4-vinyl pyridine, 2-dimethylaminoethylvinyl ether, 2-diethylaminoethylvinyl ether, 4-dimethylaminobutylvinyl ether, 4-diethylaminobutylvinyl ether and 6-dimethylaminohexylvinyl ether. These compounds may be used either individually or in combination.

[0070] The specific examples of the representative radical-polymerizable monomers or compounds having thiol (mercapto) group as the functional group reactive with carbodiimide group include those having a double bond, e.g., 2-propene-1-thiol, 3-butene-1-thiol, 4-pentene-1-thiol, 2-mercaptoethyl (meth)acrylate, 2-mercapto-1-carboxyethyl(meth)acrylate, N-(2-mercaptoethyl)acrylamide, N-(2-mercapto-1-carboxyethyl)acrylamide, N-(2-mercaptoethyl)methacrylamide, N-(4-mercaptoethyl)acrylamide, N-(7-mercaptanaphthyl)acrylamide and mono-2-mercaptoethylamide maleate; and compounds having a crosslinked structure between a compound having at least 2 functional groups (e.g., tetramethylenedithiol, hexamethylenedithiol, octamethylenedithiol or decamethylenedithiol) and monomer having

a group reactive with thiol (mercapto) group and $C=C$ double bond. These compounds may be used either individually or in combination. Thermoplastic resins having thiol (mercapto) group, e.g., modified polyvinyl alcohol having thiol (mercapto) group, are also useful for the present invention.

[0071] When 2 or more functional groups, e.g., carboxyl, hydroxyl, amino and thiol (mercapto) group, are to be incorporated, the above-described monomers having a varying reactive group may be combined with each other to produce a multi-functional copolymer. Moreover, multi-functional polymer particles containing carbodiimide group can be produced by adjusting carbodiimide resin content or reaction temperature.

[0072] For radical polymerization to produce the thermoplastic resin for the present invention, a known radical polymerization initiator may be used.

[0073] The specific examples of the representative radical polymerization initiators include peroxides, e.g., benzoyl peroxide, cumene hydroperoxide, t-butyl hydroperoxide; persulfates, e.g., sodium persulfate and ammonium persulfate; and azo-based compounds, e.g., azobisisobutyronitrile, azobismethylbutylnitrile and azobisisovaleronitrile. These compounds may be used either individually or in combination.

[0074] For production of the thermoplastic resin particles reactive with carbodiimide group, various synthesis/polymerization processes described above may be employed; they may be synthesized in the absence of solvent, e.g., block polymerization, or in the presence of solvent, e.g., solution polymerization.

[0075] The specific examples of the representative polymerization solvents include water; alcohols, e.g., methanol, ethanol, 1-propanol, 2-propanol, 1-butanol, 2-butanol, isobutyl alcohol, tert-butyl alcohol, 1-pentanol, 2-pentanol, 3-pentanol, 2-methyl-1-butanol, isopentyl alcohol, tert-pentyl alcohol, 1-hexanol, 2-methyl-1-pentanol, 4-methyl-2-pentanol, 2-ethyl butanol, 1-heptanol, 2-heptanol, 3-heptanol, 2-octanol, 2-ethyl-1-hexanol, benzyl alcohol and cyclohexanol; and ether alcohols, e.g., methyl cellosolve, ethyl cellosolve, isopropyl cellosolve, butyl cellosolve, and diethylene glycol monobutyl ether; ketones, e.g., acetone, methylethylketone, methylisobutylketone and cyclohexanone; esters, e.g., ethyl acetate, butyl acetate, ethyl propionate and cellosolve acetate; aliphatic or aromatic hydrocarbons, e.g., pentane, 2-methylbutane, n-hexane, cyclohexane, 2-methylpentane, 2,2-dimethylbutane, 2,3-dimethylbutane, heptane, n-octane, isooctane, 2,2,3-trimethylpentane, decane, nonane, cyclopentane, methylcyclopentane, methylcyclohexane, ethylcyclohexane, p-menthane, dicyclohexane, benzene, toluene, xylene and ethylbenzene; halogenated hydrocarbons, e.g., carbon tetrachloride, trichloroethylene, chlorobenzene and tetrabromoethane; ethers, e.g., ethyl ether, dimethyl ether, trioxane and tetrahydrofuran; acetals, e.g., methylal and diethyl acetal; fatty acids, e.g., formic, acetic and propionic acid; and sulfur- or nitrogen containing organic compounds, e.g., nitropropene, nitrobenzene, dimethyl amine, monoethanolamine, pyridine, dimethylformamide and dimethylsulfoxide. The solvent is not limited, and can be selected, as required, for a specific purpose of the polymerization process. These solvents may be used either individually or in combination.

[0076] A specific polymerization may incorporate, as required, one or more additives, e.g., polymer dispersant, stabilizer, emulsifier and surfactant, for production of the particles.

[0077] The specific examples of the representative additives are cited. The dispersants and stabilizers include various hydrophilic and hydrophobic ones, such as polystyrene derivatives, e.g., polyhydroxystyrene, polystyrenesulfonic acid, vinyl phenol/(meth)acrylate ester copolymer, styrene/(meth)acrylate ester copolymer and styrene/vinyl phenol/(meth)acrylate ester copolymer; poly(meth)acrylic acid and derivatives thereof, e.g., poly(meth)acrylic acid, poly(meth)acrylamide, polyacrylonitrile, polyethyl (meth)acrylate and polybutyl (meth)acrylate; polyvinyl alkyl ether derivatives, e.g., polymethyl vinyl ether, polyethyl vinyl ether, polybutyl vinyl ether and polyisobutyl vinyl ether; cellulose and derivatives thereof, e.g., cellulose, methyl cellulose, cellulose acetate, cellulose nitrate, hydroxymethyl cellulose, hydroxyethyl cellulose, hydroxypropyl cellulose and carboxymethyl cellulose; polyvinyl acetate and derivatives thereof e.g., polyvinyl alcohol, polyvinyl butyral, polyvinyl formal, and polyvinyl acetate; nitrogen-containing polymer derivatives, e.g., polyvinyl pyridine, polyvinyl pyrrolidone, polyethyleneimine and poly-2-methyl-2-oxazoline; halogenated polyvinyl derivatives, e.g., polyvinyl chloride and polyvinylidene chloride; and polysiloxane derivatives, e.g., polydimethyl siloxane. These may be used either individually or in combination.

[0078] The emulsifiers (surfactants) useful for the present invention include anionic emulsifiers, including alkyl sulfate ester salts, e.g., sodium lauryl sulfate, alkyl benzenesulfonates, e.g., sodium dodecylbenzenesulfonate, alkyl naphthalenesulfonates, fatty acid salts, alkyl phosphates, and alkylsulfosuccinates; cationic emulsifiers, including alkylamine salts, quaternary ammonium salts, alkyl betaine, and amine oxide; nonionic emulsifiers, including polyoxyethylene alkyl ether, polyoxyethylene alkyl allyl ether, polyoxyethylene alkyl phenyl ether, sorbitan/fatty acid ester, glycerin/fatty acid ester and polyoxyethylene/fatty acid ester. These may be used either individually or in combination.

[0079] When the resin or its particles are produced, a small quantity of crosslinking agent may be incorporated, depending on their purposes.

[0080] The specific examples of the representative crosslinking agents include aromatic divinyl compounds, e.g., divinyl benzene and divinyl naphthalene, ethylene glycol diacrylate, ethylene glycol dimethacrylate, triethylene glycol dimethacrylate, tetraethylene glycol dimethacrylate, 1,3-butylene glycol dimethacrylate, trimethylolpropane triacrylate, trimethylolpropane trimethacrylate, 1,4-butanediol diacrylate, neopentyl glycol diacrylate, 1,6-hexanediol diacrylate,

pentaerythritol triacrylate, pentaerythritol tetraacrylate, pentaerythritol dimethacrylate, pentaerythritol tetramethacrylate, glycerol acryloxydimethacrylate, N,N-divinyl aniline, divinyl ether, divinyl sulfide and divinyl sulfone. These may be used either individually or in combination.

4. Process for producing the hardening type reactive particles

[0081] The hardening type reactive particles of the present invention are produced first by producing a thermoplastic resin having a functional group reactive with carbodiimide group or its particles, and reacting the resin or particles with a carbodiimide resin under heating in the presence of a solvent which dissolves the carbodiimide resin but not the thermoplastic resin or particles, to obtain the semi-hardening to hardening type reactive particles without deforming shape of the particles. More specifically, the process comprises two steps: the first step in which the base particle (A) of the thermoplastic resin having a functional group is mixed with the carbodiimide compound (B) in the presence of at least one type of solvent which dissolves (B) but not (A), to have the latter impregnated only in the surface layer section or both surface layer section and inside of the former; and the subsequent second step in which the above mixture is thermally treated. This produces the semi-hardening to hardening type reactive particles.

[0082] The first step may incorporate, as required, an adequate additive, e.g., dispersant, antioxidant, stabilizer or emulsifier, in addition to the base particle (A) and carbodiimide compound (B). The specific examples of the representative additives are described. The dispersants, stabilizers and emulsifiers useful for the process are similar to those described earlier. On the other hand, the antioxidants useful for the process include those based on phenol, sulfur, phosphorus, amine, hydroquinone and hydroxylamine. These may be used either individually or in combination.

[0083] The thermoplastic resin particles having a functional group reactive with the carbodiimide group in the carbodiimide compound (i.e., carbodiimide resin) contain the functional group preferably at 30 to 700 equivalents, more preferably 50 to 700 equivalents, still more preferably 80 to 700 equivalents. The particles containing the functional group at above 700 equivalents may have deteriorated crosslinking capacity, because of an excessive distance between the molecules. When the semi-hardened particles are to be produced, however, the functional group may be present at above 700 equivalents.

[0084] The thermoplastic resin particle having a functional group is not limited, so long as it has active hydrogen group reactive with the carbodiimide group, e.g., hydroxyl, carboxyl, amino or thiol group. The particularly preferable thermoplastic resin particles are those having carboxyl or hydroxyl group.

[0085] The thermoplastic resin particles having a functional group are preferably truly or nearly spherical. However, the non-spherical ones are acceptable.

[0086] The thermoplastic resin particles preferably have a diameter of 0.01 to 10,000 μ m, more preferably 0.01 to 1,000 μ m, still more preferably 0.1 to 700 μ m.

[0087] Even when the thermoplastic resin is a film-shape composition, it can be crosslinkable when film thickness is in the above range. The films can be the hardening type reactive particles, and hence semi-hardened to hardened.

[0088] Content of the polycarbodiimide varies depending on the required carbodiimide group remaining after the crosslinking step. As a measure, it may be incorporated at 0.1 to 20 equivalents per equivalent of the functional group in the thermoplastic resin particle, preferably 0.5 to 8 equivalents, more preferably 1 to 6 equivalents.

[0089] Thermal treatment temperature at which the reaction mixture is heated for the reaction varies depending on type of the solvent used. However, it is in a range from 10 to 200°C, preferably 15 to 150°C, more preferably 20 to 130°C.

[0090] Crosslinking time is not limited, so long as it allows the crosslinking reaction to be almost completed. It largely varies depending on type and content of the carbodiimide resin used, type of the functional group in the resin (particle), viscosity and concentration of the solution, and so on. It is however around 1 to 24 hours at 40°C, preferably 6 to 24 hours.

[0091] The solvent which dissolves the carbodiimide resin but not the thermoplastic resin or its particles is at least one type of solvent selected from the group consisting of water and organic solvents. It may be adequately selected in consideration of type and content of the carbodiimide resin used, type of the thermoplastic resin (or particle) and type of the functional group it contains, purpose of the hardening type reactive particles, and so on.

[0092] The specific examples of the representative solvents include water; alcohols, e.g., methanol, ethanol, 1-propanol, 2-propanol, 1-butanol, 2-butanol, isobutyl alcohol, tert-butyl alcohol, 1-pentanol, 2-pentanol, 3-pentanol, 2-methyl-1-butanol, isopentyl alcohol, tert-pentyl alcohol, 1-hexanol, 2-methyl-1-pentanol, 4-methyl-2-pentanol, 2-ethyl butanol, 1-heptanol, 2-heptanol, 3-heptanol, 2-octanol, 2-ethyl-1-hexanol, benzyl alcohol and cyclohexanol; and ether alcohols, e.g., methyl cellosolve, ethyl cellosolve, isopropyl cellosolve, butyl cellosolve, and diethylene glycol monobutyl ether; ketones, e.g., acetone, methylethylketone, methylisobutylketone and cyclohexanone; esters, e.g., ethyl acetate, butyl acetate, ethyl propionate and cellosolve acetate; aliphatic or aromatic hydrocarbons, e.g., pentane, 2-methylbutane, n-hexane, cyclohexane, 2-methylpentane, 2,2-dimethylbutane, 2,3-dimethylbutane, heptane, n-octane, isooctane, 2,2,3-trimethylpentane, decane, nonane, cyclopentane, methylcyclopentane, methylcyclohexane, ethylcyclohexane, p-menthane, dicyclohexane, benzene, toluene, xylene and ethylbenzene; halogenated hydrocarbons, e.g., carbon

tetrachloride, trichloroethylene, chlorobenzene and tetrabromoethane; ethers, e.g., ethyl ether, dimethyl ether, trioxane and tetrahydrofuran; acetals, e.g., methylal and diethyl acetal; fatty acids, e.g., formic, acetic and propionic acid; and sulfur- or nitrogen containing organic compounds, e.g., nitropropene, nitrobenzene, dimethyl amine, monoethanolamine, pyridine, dimethylformamide and dimethylsulfoxide. The more preferable solvents are water, lower alcohols (e.g., methanol and ethanol), a mixture of water and lower alcohol, toluene, dimethylformamide (DMF), tetrahydrofuran (THF), methylethylketone (MEK), methylisobutylketone (MIBK), acetone, N-methyl pyrrolidone (NMP), dichloromethane and tetrachloroethylene. The still more preferable ones are water, lower alcohols (e.g., methanol and ethanol), a mixture of water and lower alcohol (e.g., methanol and ethanol) and toluene. The solvent is not limited, and can be selected, as required, for a specific purpose of the polymerization process. These solvents may be used either individually or in combination.

[0093] The hardening type reactive particles are produced by mixing and reacting, under heating, a thermoplastic resin particle having a group reactive with carbodiimide group (e.g., hydroxyl, amino, carboxyl or thiol group) with a carbodiimide resin in the presence of water or an organic solvent which dissolves the carbodiimide resin but not the particle. The hardening type reactive particles show performance effects of improved resistance to heat and solvents as the crosslinked particles, and excellent glueability and adhesion as the reactive particles.

[0094] Therefore, the thermoplastic resin can be hardened, have reacted carbodiimide group inside and on the surface, and hence have improved glueability and adhesion to another substance. Moreover, use of water-soluble polycarbodiimide improves dispersibility of the particles, and allows a dye or pigment having a reactive group to react with the carbodiimide to produce the fast color.

[0095] The hardening type reactive particles, keeping the above performances and being reactive crosslinked particles, can go into various areas, e.g., crosslinking agent, stabilizer for improving hydrolysis resistance, hardening agent for thermoplastic resins, adhesive agent, coating agent, paint, reinforcing material and aid for automobile and electric/electronic industries, and furniture and building materials. They are also applicable to spacers for liquid crystals, or the like.

[0096] In the process for producing the hardening type reactive particles, the carbodiimide resin can be bonded directly and simply to the spherical particles synthesized by emulsion, suspension or dispersion polymerization, or the like. Therefore, the resultant particles can be also used as those of core/shell structure. Moreover, they can be hardened with the carbodiimide resin solution, allowing the unreacted, residual carbodiimide resin to be reused repeatedly. These features make the process more economically advantageous.

EXAMPLES

[0097] The present invention is described in more detail by EXAMPLES and COMPARATIVE EXAMPLES, which by no means limit the present invention, wherein "part(s)" and "water" mean part(s) by weight and distilled water, respectively, unless otherwise stated.

[Synthesis of Carbodiimide Compound]

[0098] Synthesis of the carbodiimide Compounds for the present invention is described before EXAMPLES and COMPARATIVE EXAMPLES.

[SYNTHESIS EXAMPLE 1]

[0099] 1200g of 4,4'-dicyclohexylmethane diisocyanate (hereinafter sometimes referred to as HMDI) was reacted with 6g of a carbodiimidation catalyst (3-methyl-1-phenyl-2-phospholene-1-oxide, which was used as the carbodiimidation catalyst in all SYNTHESIS EXAMPLES) at 180°C for 21 hours, to produce 1027.3g of 4,4'-dicyclohexylmethane carbodiimide resin with isocyanate group at the terminal (degree of polymerization: 6). Then, toluene was added to the above product, to produce the carbodiimide resin solution (resin concentration: 50% by weight). It contained the carbodiimide at 262 equivalents.

[SYNTHESIS EXAMPLE 2]

[0100] 1000g of 4,4'-dicyclohexylmethane diisocyanate (HMDI) was reacted with 106g of cyclohexyl isocyanate in the presence of 11.1g of the carbodiimidation catalyst at 180°C for 36 hours, to produce 919.4g of the carbodiimide resin with cyclohexyl group at the terminal (degree of polymerization: 10). Then, toluene was added to the above product, to produce the carbodiimide resin solution (resin concentration: 50% by weight). It contained the carbodiimide at 217 equivalents.

[SYNTHESIS EXAMPLE 3]

[0101] 1200g of m-tetramethylxylylene diisocyanate (hereinafter sometimes referred to as TMXDI) was reacted with 24g of the carbodiimidation catalyst at 180°C for 26 hours, to produce 1003.3g of m-tetramethylxylylene carbodiimide with isocyanate group at the terminal (degree of polymerization: 10). Then, toluene was added to the above product, to produce the carbodiimide resin solution (resin concentration: 50% by weight). It contained the carbodiimide at 224 equivalents.

[SYNTHESIS EXAMPLE 4]

[0102] 1300g of m-tetramethylxylylene diisocyanate (TMXDI) was reacted with 26g of the carbodiimidation catalyst at 180°C for 40 hours, to produce 1068.5g of m-tetramethylxylylene carbodiimide with isocyanate group at the terminal (degree of polymerization: 80). Then, toluene was added to the above product, to produce the carbodiimide resin solution (resin concentration: 50% by weight). It contained the carbodiimide at 203 equivalents.

[SYNTHESIS EXAMPLE 5]

[0103] 1200g of 2,6-tolylene diisocyanate (TDI) was reacted with 55.2g of methanol at 50°C for 1 hour, and then in the presence of 12g of the carbodiimidation catalyst at 85°C for 6 hours in 989.7g of toluene, to produce the carbodiimide resin with methyl group at the terminal (degree of polymerization: 7) in the solution (resin concentration: 50% by weight). It contained the carbodiimide at 164 equivalents.

[SYNTHESIS EXAMPLE 6]

[0104] 1000g of 4,4'-diphenylmethane diisocyanate (hereinafter referred to as MDI) was reacted with 238g of phenyl isocyanate in the presence of 2.5g of the carbodiimidation catalyst at 70°C for 5 hours in 1018g of toluene, to produce the carbodiimide resin (degree of polymerization: 5) in the solution (resin concentration: 50% by weight). It contained the carbodiimide at 204 equivalents.

[Synthesis of Water-Soluble Carbodiimide Compound]

[SYNTHESIS EXAMPLE 7]

[0105] 800g of 4,4'-dicyclohexylmethane diisocyanate (HMDI) was reacted with 4g of a carbodiimidation catalyst at 180°C for 21 hours, to produce 4,4'-dicyclohexylmethane carbodiimide resin with isocyanate group at the terminal (degree of polymerization: 6). Next, 684.8g of the carbodiimide resin was reacted with 488.5g of polyoxyethylene monomethyl ether having a degree of polymerization m of 12 at 140°C for 6 hours. Then, 782.2g of distilled water was slowly added to the reaction effluent, to produce the light, yellowish, transparent carbodiimide resin solution (resin concentration: 60% by weight). It contained the carbodiimide at 448 equivalents.

[SYNTHESIS EXAMPLE 8]

[0106] 800g of m-tetramethylxylylene diisocyanate (TMXDI) was reacted with 16g of the carbodiimidation catalyst at 180°C for 20 hours, to produce m-tetramethylxylylene carbodiimide resin with isocyanate group at the terminal (degree of polymerization: 5). Next, 679.8g of the resultant carbodiimide resin was reacted with 177.1g of sodium hydroxypropanesulfonate at 100°C for 24 hours. Then, 571.3g of distilled water was slowly added to the reaction effluent, to produce the yellowish brown, transparent carbodiimide resin solution (resin concentration: 60% by weight). It contained the carbodiimide at 314 equivalents.

[SYNTHESIS EXAMPLE 9]

[0107] 800g of m-tetramethylxylylene diisocyanate (TMXDI) was reacted with 16g of the carbodiimidation catalyst at 180°C for 26 hours, to produce m-tetramethylxylylene carbodiimide resin with isocyanate group at the terminal (degree of polymerization: 10). Next, 668.9g of the resultant carbodiimide resin was reacted with 333.9g of polyoxyethylene monomethyl ether at 140°C for 6 hours. Then, 668.5g of distilled water was slowly added to the reaction effluent, to produce the yellowish brown, transparent carbodiimide resin solution (resin concentration: 60% by weight). It contained the carbodiimide at 336 equivalents.

[SYNTHESIS EXAMPLE 10]

[0108] 800g of 2,6-tolylene diisocyanate (TDI) was reacted preliminarily with 441.4g of polyoxyethylene monomethyl ether (degree of polymerization m: 8) at 50°C for 1 hour, and then in the presence of the presence of 8g of the carbodiimidation catalyst at 85°C for 6 hours, to produce the carbodiimide resin with the sealed terminals (degree of polymerization: 7). Then, 709.6g of distilled water was slowly added to the reaction effluent, to produce the lightly yellowish, transparent carbodiimide resin solution (resin concentration: 60% by weight). It contained the carbodiimide at 265 equivalents.

[SYNTHESIS EXAMPLE 11]

[0109] 700g of 2,6-tolylene diisocyanate (TDI) was reacted preliminarily with 418.4g of polyoxyethylene monomethyl ether (degree of polymerization m: 4) at 50°C for 1 hour, and then in the presence of the presence of 7g of the carbodiimidation catalyst at 85°C for 6 hours, to produce the carbodiimide resin with the sealed terminals (degree of polymerization: 3). Then, 657.1g of distilled water was slowly added to the reaction effluent, to produce the lightly yellowish, transparent carbodiimide resin solution (resin concentration: 60% by weight). It contained the carbodiimide at 327 equivalents. The carbodiimide compounds prepared in SYNTHESIS EXAMPLES are summarized in Table 1.

[Table 1]

Carbodiimide SYNTHESIS EXAMPLES	Diisocyanate as the starting compound	Degree of polymerization of the carbodiimide	Starting material for terminal sealing segment	NCN equivalents	Solvent
SYNTHESIS EXAMPLE 1	HMDI	6	Not used (isocyanate)	262	Toluene
SYNTHESIS EXAMPLE 2	HMDI	10	Cyclohexyl isocyanate	217	Toluene
SYNTHESIS EXAMPLE 3	TMXDI	10	Not used (isocyanate)	224	Toluene
SYNTHESIS EXAMPLE 4	TMXDI	80	Not used (isocyanate)	203	Toluene
SYNTHESIS EXAMPLE 5	TDI	7	Methanol	164	Toluene
SYNTHESIS EXAMPLE 6	MDI	5	Phenyl isocyanate	204	Toluene
SYNTHESIS EXAMPLE 7	HMDI	6	Polyoxyethylene monomethyl ether	448	Water
SYNTHESIS EXAMPLE 8	TMXDI	5	Sodium hydroxypropanesulfonate	314	Water
SYNTHESIS EXAMPLE 9	TMXDI	10	Polyoxyethylene monomethyl ether	336	Water
SYNTHESIS EXAMPLE 10	TDI	7	Polyoxyethylene monomethyl ether	265	Water
SYNTHESIS EXAMPLE 11	TDI	3	Polyoxyethylene monomethyl ether	327	Water

[PARTICLE EXAMPLE 1, prepared on a trial basis]

(COMPARATIVE EXAMPLE 1)

[0110] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 18 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 70°C.

EP 1 344 795 A2

Styrene	60.0 parts
Methacrylic acid	40.0 parts
Methanol	100.0 parts
Azobis-2-methylbutylonitrile (ABNE)	1.0 part

[0111] The resultant reactive polymer solution was left to cool and collected on a stainless tray. It was then dried at 60°C for around 24 hours in a drier, to produce the resin containing carboxyl group. It was crushed and classified by known machines into the particles.

[0112] These particles had a volume-average particle diameter of 41μm, determined by a particle size distribution analyzer (Nikkiso's Microtrack 9320HRA). They had the smallest particle diameter of 0.1μm and largest particle diameter of 78μm, determined by SEM analysis. These particles were named COMPARATIVE EXAMPLE 1 particles.

[PARTICLE EXAMPLE 2, prepared on a trial basis]

(COMPARATIVE EXAMPLE 2)

[0113] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 18 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 70°C.

Styrene	50.0 parts
Acrylic acid	50.0 parts
Methanol	100.0 parts
Azobis-isobutylonitrile (AIBN)	3.0 parts

[0114] The resultant reactive polymer solution was left to cool and collected on a stainless tray. It was then dried at 60°C for around 24 hours in a drier, to produce the resin containing carboxyl group. It was crushed and classified by known machines into the particles.

[0115] These particles had a volume-average particle diameter of 164μm, determined by a particle size distribution analyzer (Nikkiso's Microtrack 9320HRA). They had the smallest particle diameter of 6.5μm and largest particle diameter of 1020μm, determined by SEM analysis. These particles were named COMPARATIVE EXAMPLE 2 particles.

[PARTICLE EXAMPLE 3, prepared on a trial basis]

(COMPARATIVE EXAMPLE 3)

[0116] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 18 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 70°C.

Methyl methacrylate	50.0 parts
Acrylic acid	50.0 parts
Methanol	100.0 parts
Azobis-isobutylonitrile (AIBN)	4.0 parts

[0117] The resultant reactive polymer solution was left to cool and collected on a stainless tray. It was then dried at 60°C for around 24 hours in a drier, to produce the resin containing carboxyl group. It was crushed and classified by known machines into the particles.

[0118] These particles had a volume-average particle diameter of 282μm, determined by a particle size distribution analyzer (Nikkiso's Microtrack 9320HRA). They had the smallest particle diameter of 95μm and largest particle diameter of 710μm, determined by SEM analysis. These particles were named COMPARATIVE EXAMPLE 3 particles.

[PARTICLE EXAMPLE 4, prepared on a trial basis]

(COMPARATIVE EXAMPLE 4)

[0119] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around

EP 1 344 795 A2

18 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 70°C.

Styrene	30.0 parts
Acrylic acid	70.0 parts
Methanol	100.0 parts
Azobis-isobutyronitrile (AIBN)	2.0 parts

[0120] The resultant reactive polymer solution was left to cool and collected on a stainless tray. It was then dried at 60°C for around 24 hours in a drier, to produce the resin containing carboxyl group. It was crushed and classified by known machines into the particles.

[0121] These particles had a volume-average particle diameter of 73µm, determined by a particle size distribution analyzer (Nikkiso's Microtrack 9320HRA). They had the smallest particle diameter of 6µm and largest particle diameter of 211µm, determined by SEM analysis. These particles were named COMPARATIVE EXAMPLE 4 particles.

[PARTICLE EXAMPLE 5, prepared on a trial basis]

(COMPARATIVE EXAMPLE 5)

[0122] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 18 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 70°C.

Acrylic acid	100.0 parts
Methanol	100.0 parts
Azobis-isobutyronitrile (AIBN)	3.0 parts

[0123] The resultant reactive polymer solution was left to cool and collected on a stainless tray. It was then dried at 60°C for around 24 hours in a drier, to produce the resin containing carboxyl group. It was crushed and classified by known machines into the particles.

[0124] These particles had a volume-average particle diameter of 24µm, determined by a particle size distribution analyzer (Nikkiso's Microtrack 9320HRA). They had the smallest particle diameter of 1.1µm and largest particle diameter of 65µm, determined by SEM analysis. These particles were named COMPARATIVE EXAMPLE 5 particles.

[PARTICLE EXAMPLE 6, prepared on a trial basis]

(COMPARATIVE EXAMPLE 6)

[0125] Coarse particles of polyvinyl alcohol (Kuraray's PVA-210, partly saponified, 88% by mol) were crushed and classified by known machines into the fine particles.

[0126] These particles had a volume-average particle diameter of 48µm, determined by a particle size distribution analyzer (Nikkiso's Microtrack 9320HRA). They had the smallest particle diameter of 1.2µm and largest particle diameter of 103µm, determined by SEM analysis. These particles were named COMPARATIVE EXAMPLE 6 particles.

[PARTICLE EXAMPLE 7, prepared on a trial basis]

(COMPARATIVE EXAMPLE 7)

[0127] Coarse particles of polyvinyl alcohol (Kuraray's PVA-117, totally saponified) were crushed and classified by known machines into the fine particles.

[0128] These particles had a volume-average particle diameter of 21µm, determined by a particle size distribution analyzer (Nikkiso's Microtrack 9320HRA). They had the smallest particle diameter of 1.2µm and largest particle diameter of 74µm, determined by SEM analysis. These particles were named COMPARATIVE EXAMPLE 7 particles.

[PARTICLE EXAMPLE 8, prepared on a trial basis]

(COMPARATIVE EXAMPLE 8)

- 5 [0129] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 18 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 70°C.

Styrene	90.0 parts
Acrylic acid	10.0 parts
THF	100.0 parts
Azobis-isobutyronitrile (AIBN)	2.0 parts

- 10 [0130] The resultant reactive polymer solution was left to cool and collected on a stainless tray. It was then dried at 60°C for around 24 hours in a drier, to produce the resin containing carboxyl group. It was crushed and classified by known machines into the particles.

[0131] These particles had a volume-average particle diameter of 71 μ m, determined by a particle size distribution analyzer (Nikkiso's Microtrack 9320HRA). They had the smallest particle diameter of 4.2 μ m and largest particle diameter of 229 μ m, determined by SEM analysis. These particles were named COMPARATIVE EXAMPLE 8 particles.

15 [0132] These PARTICLE EXAMPLES 1 to 8, prepared on a trial basis, are summarized in Table 2.

[Table 2]

	Functional group in the particle	Equivalents of the functional group	Starting compounds used
25 PARTICLE EXAMPLE 1	Carboxyl	215/COOH	Styrene and methacrylic acid
PARTICLE EXAMPLE 2	Carboxyl	144/COOH	Styrene and acrylic acid
30 PARTICLE EXAMPLE 3	Carboxyl	144/COOH	Methyl methacrylate and acrylic acid
PARTICLE EXAMPLE 4	Carboxyl	103/COOH	Styrene and acrylic acid
PARTICLE EXAMPLE 5	Carboxyl	72/COOH	Acrylic acid
35 PARTICLE EXAMPLE 6	Hydroxyl	56/OH	PVA
PARTICLE EXAMPLE 7	Hydroxyl	44/OH	PVA
PARTICLE EXAMPLE 8	Carboxyl	720/COOH	Styrene and acrylic acid

40 (EXAMPLE 1)

[0133] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 1	78.0 parts
Toluene	52.0 parts

- 45 [0134] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

50 (EXAMPLE 2)

[0135] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around

EP 1 344 795 A2

15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 55°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	7.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 2	56.0 parts
Toluene	84.0 parts

[0136] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 3)

[0137] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 3	84.0 parts
Toluene	56.0 parts

[0138] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 4)

[0139] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 65°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 4	56.0 parts
Toluene	84.0 parts

[0140] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 5)

[0141] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 45°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 5	60.0 parts
Toluene	90.0 parts

[0142] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 6)

[0143] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 6	60.0 parts
Toluene	90.0 parts

[0144] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 7)

[0145] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 7	28.0 parts
Methanol	77.0 parts
Water	66.0 parts

[0146] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 8)

[0147] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 55°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 8	48.0 parts
Methanol	58.0 parts
Water	39.0 parts

[0148] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 9)

[0149] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 9	52.0 parts

(continued)

Methanol	62.0 parts
Water	41.0 parts

[0150] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 10)

[0151] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 40°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	7.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 10	43.0 parts
Methanol	52.0 parts
Water	35.0 parts

[0152] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 11)

[0153] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 35°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 1, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 11	62.0 parts
Methanol	43.0 parts
Water	18.0 parts

[0154] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 12)

[0155] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 1	72.0 parts
Toluene	48.0 parts

[0156] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 13)

[0157] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 2	76.0 parts
Toluene	114.0 parts

[0158] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 14)

[0159] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 55°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 3	78.0 parts
Toluene	52.0 parts

[0160] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 15)

[0161] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 65°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 4	46.0 parts
Toluene	69.0 parts

[0162] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 16)

[0163] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 40°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 5	54.0 parts
Toluene	81.0 parts

[0164] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum

EP 1 344 795 A2

filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 17)

[0165] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 45°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 6	46.0 parts
Toluene	69.0 parts

[0166] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 18)

[0167] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 55°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	3.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 7	32.0 parts
Water	158.0 parts

[0168] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 19)

[0169] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	3.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 8	43.0 parts
Water	87.0 parts

[0170] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 20)

[0171] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 65°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	3.0 parts
---	-----------

(continued)

Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 9	58.0 parts
Water	117.0 parts

[0172] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 21)

[0173] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 30°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 10	62.0 parts
Water	61.0 parts

[0174] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 22)

[0175] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 25°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 2, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 11	95.0 parts
Water	48.0 parts

[0176] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 23)

[0177] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 3, prepared on a trial basis	4.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 1	72.0 parts
Toluene	48.0 parts

[0178] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 24)

[0179] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 70°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 3, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 4	84.0 parts
Toluene	56.0 parts

[0180] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 25)

[0181] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 3, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 6	70.0 parts
Toluene	105.0 parts

[0182] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 26)

[0183] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 45°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 3, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 7	52.0 parts
Water	103.0 parts

[0184] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 27)

[0185] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 20°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 3, prepared on a trial basis	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 10	62.0 parts
Water	61.0 parts

[0186] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution

EP 1 344 795 A2

and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 28)

[0187] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 4, prepared on a trial basis	3.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 1	122.0 parts
Toluene	81.0 parts

[0188] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 29)

[0189] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 65°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 4, prepared on a trial basis	4.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 4	78.0 parts
Toluene	52.0 parts

[0190] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 30)

[0191] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 4, prepared on a trial basis	4.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 6	80.0 parts
Toluene	120.0 parts

[0192] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 31)

[0193] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 4, prepared on a trial basis	2.0 parts
---	-----------

(continued)

Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 7	72.0 parts
Water	143.0 parts

[0194] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 32)

[0195] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 40°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 4, prepared on a trial basis	4.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 10	85.0 parts
Water	85.0 parts

[0196] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 33)

[0197] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 55°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 5, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 2	84.0 parts
Toluene	126.0 parts

[0198] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 34)

[0199] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 65°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 5, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 3	124.0 parts
Toluene	83.0 parts

[0200] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 35)

[0201] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 5, prepared on a trial basis	3.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 5	109.0 parts
Toluene	73.0 parts

[0202] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 36)

[0203] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 5, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 6	68.0 parts
Toluene	102.0 parts

[0204] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 37)

[0205] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 105°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 6, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 1	112.0 parts
Toluene	75.0 parts

[0206] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 38)

[0207] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 110°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 6, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 3	128.0 parts
Toluene	85.0 parts

[0208] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum

EP 1 344 795 A2

filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 39)

[0209] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 100°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 6, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 5	94.0 parts
Toluene	63.0 parts

[0210] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 40)

[0211] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 100°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 7, prepared on a trial basis	3.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 5	134.0 parts
Toluene	89.0 parts

[0212] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(EXAMPLE 41)

[0213] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 95°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 7, prepared on a trial basis	2.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 6	112.0 parts
Toluene	112.0 parts

[0214] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed an absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(COMPARATIVE EXAMPLE 9)

[0215] A 300mL flask was charged with the mixture of the following composition all at once. However, PARTICLE EXAMPLE 8 was dissolved in toluene.

PARTICLE EXAMPLE 8, prepared on a trial basis	8.0 parts
---	-----------

EP 1 344 795 A2

(continued)

Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 1	30.0 parts
Toluene	120.0 parts

(COMPARATIVE EXAMPLE 10)

[0216] A 300mL flask was charged with the mixture of the following composition all at once. However, PARTICLE EXAMPLE 8 was dissolved in toluene.

PARTICLE EXAMPLE 8, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 2	24.0 parts
Toluene	96.0 parts

(COMPARATIVE EXAMPLE 11)

[0217] A 300mL flask was charged with the mixture of the following composition all at once. However, PARTICLE EXAMPLE 8 was dissolved in toluene.

PARTICLE EXAMPLE 8, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 3	24.0 parts
Toluene	96.0 parts

(COMPARATIVE EXAMPLE 12)

[0218] A 300mL flask was charged with the mixture of the following composition all at once. However, PARTICLE EXAMPLE 8 was dissolved in toluene.

PARTICLE EXAMPLE 8, prepared on a trial basis	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 4	22.0 parts
Toluene	88.0 parts

(COMPARATIVE EXAMPLE 13)

[0219] A 300mL flask was charged with the mixture of the following composition all at once. However, PARTICLE EXAMPLE 8 was dissolved in toluene.

PARTICLE EXAMPLE 8, prepared on a trial basis	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 5	22.0 parts
Toluene	88.0 parts

(COMPARATIVE EXAMPLE 14)

[0220] A 300mL flask was charged with the mixture of the following composition all at once. However, PARTICLE EXAMPLE 8 was dissolved in toluene.

PARTICLE EXAMPLE 8, prepared on a trial basis	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 6	22.0 parts
Toluene	88.0 parts

(COMPARATIVE EXAMPLE 15)

[0221] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 8, prepared on a trial basis	6.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 7	25.0 parts
Methanol	95.0 parts
Water	31.0 parts

[0222] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed a trace quantity of absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(COMPARATIVE EXAMPLE 16)

[0223] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 8, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 8	23.0 parts
Methanol	88.0 parts
Water	29.0 parts

[0224] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed a trace quantity of absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(COMPARATIVE EXAMPLE 17)

[0225] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 65°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 8, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 9	25.0 parts
Methanol	95.0 parts
Water	31.0 parts

[0226] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed a trace quantity of absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(COMPARATIVE EXAMPLE 18)

[0227] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 35°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 8, prepared on a trial basis	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 10	25.0 parts
Methanol	95.0 parts
Water	31.0 parts

[0228] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution

and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed a trace quantity of absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

(COMPARATIVE EXAMPLE 19)

[0229] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 30°C, to prepare the carbodiimide-containing, crosslinked particle solution.

PARTICLE EXAMPLE 8, prepared on a trial basis	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 11	25.0 parts
Methanol	95.0 parts
Water	31.0 parts

[0230] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles showed a trace quantity of absorption band peak relevant to carbodiimide group at a wavelength of around 2150 (1/cm), determined by a Fourier transform infrared spectrometer (Shimadzu Corp.'s FT-IR8200PC).

[0231] EXAMPLES 1 to 41 are summarized in Table 3, and COMPARATIVE EXAMPLES 1 to 19 in Table 4.

[Table 3]

EXAMPLES	Starting diisocyanate compound for carbodiimidation	Content of carbodiimide (equivalents), (NCN/functional group)	Reaction temperature (°C)	Solvents	Solution concentration (% by weight) (Total solution-Solvent) / Total solution × 100
1	HMDI	4	50	Toluene	34.1
2	HMDI	4	55	Toluene	23.8
3	TMXDI	4	60	Toluene	34.7
4	TMXDI	3	65	Toluene	25.3
5	TDI	4	45	Toluene	25.0
6	MDI	4	50	Toluene	24.1
7	HMDI	4	50	Water/methanol, mixture	11
8	TMXDI	4	55	Water/methanol, mixture	22.7
9	TMXDI	4	60	Water/methanol, mixture	22.5
10	TDI	3	40	Water/methanol, mixture	24.1
11	TDI	3	35	Water/methanol, mixture	34.4
12	HMDI	4	50	Toluene	32.8
13	HMDI	5	60	Toluene	22.1
14	TMXDI	5	55	Toluene	32.6
15	TMXDI	2	65	Toluene	25.2
16	TDI	3	40	Toluene	24.5

[Table 3] (continued)

EXAMPLES	Starting diisocyanate compound for carbodiimidation	Content of carbodiimide (equivalents), (NCN/functional group)	Reaction temperature (°C)	Solvents	Solution concentration (% by weight) (Total solution-Solvent) / Total solution × 100
17	MDI	2	45	Toluene	25.2
18	HMDI	2	55	Water	11.4
19	TMXDI	4	60	Water	21.8
20	TMXDI	5	65	Water	21.3
21	TDI	4	30	Water	32.8
22	TDI	5	25	Water	41.9
23	HMDI	5	60	Toluene	32.3
24	TMXDI	6	70	Toluene	32.4
25	MDI	5	50	Toluene	22.2
26	HMDI	5	45	Water	21
27	TDI	4	20	Water	32.8
28	HMDI	8	60	Toluene	31.1
29	TMXDI	5	65	Toluene	32.1
30	MDI	5	50	Toluene	21.6
31	HMDI	5	50	Water	20.7
32	TDI	5	40	Water	31.6
33	HMDI	7	55	Toluene	20.8
34	TMXDI	10	65	Toluene	30.6
35	TDI	8	50	Toluene	31.1
36	MDI	6	50	Toluene	20.9
37	HMDI	6	105	Toluene	30.7
38	TMXDI	8	110	Toluene	30.7
39	TDI	6	100	Toluene	30.8
40	TDI	6	100	Toluene	31
41	MDI	6	95	Toluene	25.7

[Table 4]

COMPARATIVE EXAMPLES	Starting diisocyanate compound for carbodiimidation	Content of carbodiimide (equivalents), (NCN/ functional group)	Reaction temperature (°C)	Solvents	Solution concentration (% by weight) (Total solution- Solvent)/Total solution × 100
1	No carbodiimide was contained in the particle		-	-	-
2					
3					
4					
5					
6					
7					
8					
9	HMDI	5	-	Toluene	14.6
10	HMDI	5		Toluene	15.6
11	TMXDI	5		Toluene	15.6
12	TMXDI	4		Toluene	17.5
13	TDI	5		Toluene	17.5
14	MDI	4		Toluene	17.5
15	HMDI	4	60	Water/ methanol, mixture	13.4
16	TMXDI	4	60	Water/ methanol, mixture	14.9
17	TMXDI	4	65	Water/ methanol, mixture	14.5
18	TDI	4	35	Water/ methanol, mixture	15.5
19	TDI	4	30	Water/ methanol, mixture	14.5

(Evaluation test 1)

[0232] A 300mL flask was charged with 1g of the particles prepared in each of EXAMPLES 1 to 41 and COMPARATIVE EXAMPLES 1 to 19, water and 100mL of an organic solvent described in Table 5 or 6. Each of the resultant mixtures was stirred at normal temperature for 30 minutes. Then, it was visually observed to confirm its resistance to solvents, and also analyzed by an SEM (Hitachi's S-2150) to confirm the particle shape. The evaluation results are given in Tables 5 and 6.

[Table 5]

Solvents	Water		Methanol		Ethanol		Toluene		DMF		THF		MEK		NMP		Acetone		Dichloromethane	
	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis
Test 1																				
EXAMPLE 1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
2	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
3	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
4	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
5	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
6	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
7	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
8	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
9	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
10	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
11	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
12	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
13	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
14	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
15	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
16	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
17	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
18	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
19	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
20	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
21	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
22	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
23	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
24	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
25	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
26	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
27	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
28	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
29	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
30	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
31	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
32	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
33	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
34	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
35	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
36	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
37	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
38	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
39	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
40	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 41	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1

O: Dispersed
 1: Particle retaining shape of the base particle
 F: Particle dissolved before it was synthesized
 X: Dissolved
 Q: Particle no longer retaining shape of the base particle

[Table 6]

Solvents	Water		Methanol		Ethanol		Toluene		DMF		THF		MEK		NMP		Acetone		Dichloromethane	
	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis
Test 1																				
COMPARATIVE EXAMPLE 1	O	1	x	0	x	0	O	1	x	0	x	0	x	0	x	0	x	0	O	1
2	O	1	x	0	x	0	O	1	x	0	x	0	x	0	x	0	x	0	O	1
3	O	1	x	0	x	0	O	1	x	0	x	0	x	0	x	0	x	0	x	0
4	O	1	x	0	x	0	O	1	x	0	x	0	x	0	x	0	x	0	O	0
5	Δ	0	x	0	x	0	O	1	x	0	x	0	x	0	x	0	x	0	O	0
6	Δ	0	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
7	*	*	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
8	O	1	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0
9																				
10																				
11																				
12																				
13																				
14																				
15	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0	x	0
16	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0	x	0
17	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0	x	0
18	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0	x	0
COMPARATIVE EXAMPLE 19	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0	x	0

O: Dispersed
 Δ: Partly dispersed
 1: Particle retaining shape of the base particle
 *: Normal temperature O, Elevated temperature x
 F: Particle dissolved before it was synthesized
 x: Dissolved
 0: Particle no longer retaining shape of the base particle

EP 1 344 795 A2

(Evaluation test 2)

[0233] 1g of the particles prepared in each of EXAMPLES 1 to 41 and COMPARATIVE EXAMPLES 1 to 19, put on an aluminum Petri dish, was cured for 1 hour in a drier kept at 180°C, to confirm the residual particles on the dish. The residual particles were analyzed by an SEM (Hitachi's S-2150) to confirm their shape. The evaluation results are given in Table 7.

[Table 7]

Test 2	Visual observation	SEM analysis	Test 2	Visual observation	SEM analysis
EXAMPLE 1	○	2	EXAMPLE 31	○	2
EXAMPLE 2	○	2	EXAMPLE 32	○	2
EXAMPLE 3	○	2	EXAMPLE 33	○	2
EXAMPLE 4	○	2	EXAMPLE 34	○	2
EXAMPLE 5	○	2	EXAMPLE 35	○	2
EXAMPLE 6	○	2	EXAMPLE 36	○	2
EXAMPLE 7	○	2	EXAMPLE 37	○	2
EXAMPLE 8	○	2	EXAMPLE 38	○	2
EXAMPLE 9	○	2	EXAMPLE 39	○	2
EXAMPLE 10	○	2	EXAMPLE 40	○	2
EXAMPLE 11	○	2	EXAMPLE 41	○	2
EXAMPLE 12	○	2	COMPARATIVE EXAMPLE 1	Δ	1
EXAMPLE 13	○	2	COMPARATIVE EXAMPLE 2	×	0
EXAMPLE 14	○	2	COMPARATIVE EXAMPLE 3	×	0
EXAMPLE 15	○	2	COMPARATIVE EXAMPLE 4	×	0
EXAMPLE 16	○	2	COMPARATIVE EXAMPLE 5	×	0
EXAMPLE 17	○	2	COMPARATIVE EXAMPLE 6	○	2
EXAMPLE 18	○	2	COMPARATIVE EXAMPLE 7	○	2
EXAMPLE 19	○	2	COMPARATIVE EXAMPLE 8	×	0
EXAMPLE 20	○	2	COMPARATIVE EXAMPLE 9	F	
EXAMPLE 21	○	2	COMPARATIVE EXAMPLE 10	F	
EXAMPLE 22	○	2	COMPARATIVE EXAMPLE 11	F	
EXAMPLE 23	○	2	COMPARATIVE EXAMPLE 12	F	
EXAMPLE 24	○	2	COMPARATIVE EXAMPLE 13	F	

[Table 7] (continued)

Test 2	Visual observation	SEM analysis	Test 2	Visual observation	SEM analysis
EXAMPLE 25	○	2	COMPARATIVE EXAMPLE 14	F	
EXAMPLE 26	○	2	COMPARATIVE EXAMPLE 15	Δ	1
EXAMPLE 27	○	2	COMPARATIVE EXAMPLE 16	Δ	1
EXAMPLE 28	○	2	COMPARATIVE EXAMPLE 17	Δ	1
EXAMPLE 29	○	2	COMPARATIVE EXAMPLE 18	Δ	1
EXAMPLE 30	○	2	COMPARATIVE EXAMPLE 19	Δ	1
○: Particle retaining its shape Δ: Particle dissolved to some extent ×: Particle dissolved into a plate shape 2: Particle retaining its original shape 1: Particle deformed 0: Particle no longer retaining its particular shape F: Particle dissolved before it was synthesized					

[SPHERICAL PARTICLE SYNTHESIS EXAMPLE 1] (COMPARATIVE EXAMPLE 20)

[0234] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 80°C, after dissolved oxygen was purged with nitrogen, to prepare the styrene/methacrylate copolymer particle solution.

Styrene	48.2 parts
Methacrylic acid	20.6 parts
Methanol	162.0 parts
Ethanol	40.5 parts
Water	67.5 parts
Azobis-2-methylbutylnitrile (ABNE)	3.1 part
15% by weight of methanol solution of PVP 8K-120)	82.0 parts

[0235] These particles had a volume-average particle diameter of 1.9 μ m, determined by particle size distribution analysis. They were truly spherical, having the smallest particle diameter of 0.29 μ m and largest particle diameter of 3.69 μ m, determined by SEM analysis. Part of the particle solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. Part of these particles were named COMPARATIVE EXAMPLE 20 particles.

[SPHERICAL PARTICLE SYNTHESIS EXAMPLE 2] (COMPARATIVE EXAMPLE 21)

[0236] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 80°C, after dissolved oxygen was purged with nitrogen, to prepare the styrene/acrylate copolymer particle solution.

Styrene	48.2 parts
Acrylic acid	20.6 parts
Methanol	162.0 parts
Ethanol	54.0 parts
Water	54.0 parts
Azobis-2-methylbutylnitrile (ABNE)	3.1 parts
Styrene/methacrylate copolymer resin solution	60.0 parts

(The styrene/methacrylate copolymer resin solution was a 40% by weight methanol solution of styrene/2-hydroxyethyl methacrylate (2/8).

[0237] These particles had a volume-average particle diameter of 12.9 μ m, determined by particle size distribution analysis. They were truly spherical, having the smallest particle diameter of 5.9 μ m and largest particle diameter of 37 μ m, determined by SEM analysis. Part of the particle solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. Part of these particles were named COMPARATIVE EXAMPLE 21 particles.

[SPHERICAL PARTICLE SYNTHESIS EXAMPLE 3] (COMPARATIVE EXAMPLE 22)

[0238] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 70°C, after dissolved oxygen was purged with nitrogen, to prepare the styrene/methacrylate copolymer particle solution.

Styrene	44.7 parts
Methacrylic acid	24.1 parts
Methanol	94.5 parts
Ethanol	87.8 parts
Water	87.8 parts
Azobis-isobutyronitrile (AIBN)	8.1 parts
Styrene/methacrylate copolymer resin solution	80.0 parts

(The styrene/methacrylate copolymer resin solution was a 40% by weight methanol solution of styrene/2-hydroxyethyl methacrylate (1/9).

[0239] These particles had a volume-average particle diameter of 10.5 μ m, determined by particle size distribution analysis. They were truly spherical, having the smallest particle diameter of 5.8 μ m and largest particle diameter of 31 μ m, determined by SEM analysis. Half of the particle solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles were named COMPARATIVE EXAMPLE 22 particles.

[SPHERICAL PARTICLE SYNTHESIS EXAMPLE 4] (COMPARATIVE EXAMPLE 23)

[0240] A 500mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 62°C, after dissolved oxygen was purged with nitrogen, to prepare the styrene/methacrylate copolymer particle solution.

Styrene	61.9 parts
Methacrylic acid	6.9 parts
Methanol	90.3 parts
Azobis-isobutyronitrile (AIBN)	1.6 parts
Styrene/methacrylate copolymer resin solution	90.7 parts

(The styrene/methacrylate copolymer resin solution was a 40% by weight methanol solution of styrene/2-hydroxyethyl methacrylate (1/9).

[0241] These particles had a volume-average particle diameter of 7.6 μ m, determined by particle size distribution analysis. They were truly spherical, having the smallest particle diameter of 3.2 μ m and largest particle diameter of 13.2 μ m, determined by SEM analysis. The particle solution was treated by around 3 to 5 cycles of washing with methanol and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles. These particles were named COMPARATIVE EXAMPLE 23 particles.

[0242] SYNTHESIS EXAMPLES 1 to 4 to prepare the spherical particles are summarized in Table 8.

[Table 8]

	Functional group in the particle	Equivalents of the functional group	Starting compounds used
SPHERICAL PARTICLE EXAMPLE 1	Carboxyl	287/COOH	Styrene and methacrylic acid
SPHERICAL PARTICLE EXAMPLE 2	Carboxyl	240/COOH	Styrene and acrylic acid
SPHERICAL PARTICLE EXAMPLE 3	Carboxyl	246/COOH	Styrene and methacrylic acid
SPHERICAL PARTICLE EXAMPLE 4	Carboxyl	860/COOH	Styrene and methacrylic acid

(EXAMPLE 42)

[0243] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 40°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particles prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 1	5.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 7	65.0 parts
Methanol	109.2 parts
Water	20.8 parts

[0244] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(EXAMPLE 43)

[0245] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 25°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particles prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 1	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 10	37.0 parts
Methanol	62.2 parts
Water	11.8 parts

[0246] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(EXAMPLE 44)

[0247] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 45°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particle solution prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 2	30.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 7	74.7 parts
Methanol	67.2 parts
Water	37.3 parts

[0248] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(EXAMPLE 45)

[0249] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 45°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particle solution prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 2	30.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 8	65.5 parts
Methanol	78.6 parts
Water	52.4 parts

[0250] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(EXAMPLE 46)

[0251] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particles prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 3	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 1	68.2 parts
Toluene	102.3 parts

[0252] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(EXAMPLE 47)

[0253] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particles prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 3	8.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 3	58.2 parts
Toluene	135.8 parts

[0254] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(EXAMPLE 48)

[0255] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 30°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particles prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 3	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 6	66.4 parts
Toluene	99.6 parts

[0256] Next, the solution was treated by around 3 to 5 cycles of washing with toluene and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(EXAMPLE 49)

[0257] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 60°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particle solution prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 3	30.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 8	63.8 parts
Methanol	76.6 parts
Water	51.1 parts

[0258] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(EXAMPLE 50)

[0259] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 30°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particle solution prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 3	40.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 10	57.5 parts
Methanol	56.4 parts
Water	1.2 parts

[0260] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(COMPARATIVE EXAMPLE 24)

[0261] A 300mL flask was charged with the mixture of the following composition all at once. However, the particles were dissolved.

Particles prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 4	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 5	30.5 parts
Toluene	122.1 parts

(COMPARATIVE EXAMPLE 25)

[0262] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 50°C, to prepare the carbodiimide-containing, crosslinked particle solution.

Particles prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 4	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 7	43.3 parts
Methanol	72.8 parts
Water	13.9 parts

[0263] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

(COMPARATIVE EXAMPLE 26)

[0264] A 300mL flask was charged with the mixture of the following composition all at once, and heated for around 15 hours in a flow of nitrogen with stirring by an agitator in an oil bath kept at 30°C, to prepare the carbodiimide-

containing, crosslinked particle solution.

Particles prepared in SPHERICAL PARTICLE SYNTHESIS EXAMPLE 4	10.0 parts
Carbodiimide resin solution prepared in SYNTHESIS EXAMPLE 10	20.6 parts
Methanol	77.5 parts
Water	24.9 parts

[0265] Next, the solution was treated by around 3 to 5 cycles of washing with a water/methanol (3/7) mixed solution and filtration by a known vacuum filtration unit, and dried under a vacuum to prepare the crosslinked particles.

[0266] EXAMPLES 42 to 50 are summarized in Table 9, and COMPARATIVE EXAMPLES 20 to 26 in Table 10.

[Table 9]

EXAMPLES	Starting diisocyanate compound for carbodiimidation	Content of carbodiimide (equivalents) (NCN/functional group)	Reaction temperature (°C)	Solvents	Solution concentration (% by weight) (Total solution-Solvent) / Total solution × 100
42	HMDI	5	40	Water/methanol, mixture	22.0
43	TDI	3	25	Water/methanol, mixture	25.4
44	HMDI	4	45	Water/methanol, mixture	24.3
45	TMXDI	5	45	Water/methanol, mixture	20.0
46	HMDI	4	50	Toluene	23.6
47	TMXDI	4	60	Toluene	18.4
48	MDI	4	30	Toluene	24.5
49	TMXDI	5	60	Water/methanol, mixture	20.0
50	TDI	4	30	Water/methanol, mixture	27.4

[Table 10]

COMPARATIVE EXAMPLES	Starting diisocyanate compound for carbodiimidation	Content of carbodiimide (equivalents) (NCN/functional group)	Reaction temperature (°C)	Solvents	Solution concentration (% by weight) (Total solution-Solvent) / Total solution × 100
20	No carbodiimide was contained in the particle		-	-	-
21					
22					
23					
24	TDI	8	-	Toluene	15.5

[Table 10] (continued)

COMPARATIVE EXAMPLES	Starting diisocyanate compound for carbodiimidation	Content of carbodiimide (equivalents) (NCN/ functional group)	Reaction temperature (°C)	Solvents	Solution concentration (% by weight) (Total solution- Solvent)/Total solution × 100
25	HMDI	5	50	Water/ methanol, mixture	25.7
26	TDI	4	30	Water/ methanol, mixture	16.8

(Evaluation test 3)

[0267] A 300mL flask was charged with 1g of the particles prepared in each of EXAMPLES 42 to 50 and COMPARATIVE EXAMPLES 20 to 26, water and 100mL of an organic solvent described in Table 11. Each of the resultant mixtures was stirred at normal temperature for 30 minutes. Then, it was visually observed to confirm its resistance to solvents, and also analyzed by an SEM (Hitachi's S-2150) to confirm the particle shape. The evaluation results are given in Table 11.

[Table 11]

Solvents	Water		Methanol		Ethanol		Toluene		DMF		THF		MEK		NMP		Acetone		Dichloromethane	
	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis	Visual observation	SEM analysis
Test 3																				
EXAMPLE 42	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 43	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 44	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 45	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 46	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 47	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 48	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 49	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
EXAMPLE 50	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1	O	1
COMPARATIVE EXAMPLE 20	O	1	x	0	x	0	Δ	0	x	0	x	0	x	0	x	0	x	0	x	0
COMPARATIVE EXAMPLE 21	O	1	x	0	x	0	Δ	0	x	0	x	0	x	0	x	0	x	0	x	0
COMPARATIVE EXAMPLE 22	O	1	x	0	x	0	O	1	x	0	x	0	x	0	x	0	x	0	Δ	0
COMPARATIVE EXAMPLE 23	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0	x	0
COMPARATIVE EXAMPLE 24																				
COMPARATIVE EXAMPLE 25	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0	x	0
COMPARATIVE EXAMPLE 26	O	1	O	1	O	1	x	0	x	0	x	0	x	0	x	0	x	0	x	0

F

O: Dispersed
 1: Particle retaining shape of the base particle
 *: Normal temperature O, Elevated temperature x
 F: Particle dissolved before it was synthesized
 Δ: Partly dispersed
 x: Dissolved
 0: Particle no longer retaining shape of the base particle

(Evaluation test 4)

[0268] 1g of the particles prepared in each of EXAMPLES 42 to 50 and COMPARATIVE EXAMPLES 20 to 26, put on an aluminum Petri dish, was cured for 1 hour in a drier kept at 180°C, to confirm the residual particles on the dish. The residual particles were analyzed by an SEM (Hitachi's S-2150) to confirm their shape. The evaluation results are given in Table 12.

[Table 12]

Test 4	Visual observation	SEM analysis	Test 4	Visual observation	SEM analysis
EXAMPLE 42	○	2	COMPARATIVE EXAMPLE 20	×	0
EXAMPLE 43	○	2	COMPARATIVE EXAMPLE 21	×	0
EXAMPLE 44	○	2	COMPARATIVE EXAMPLE 22	△	1
EXAMPLE 45	○	2	COMPARATIVE EXAMPLE 23	×	0
EXAMPLE 46	○	2	COMPARATIVE EXAMPLE 24	F	
EXAMPLE 47	○	2	COMPARATIVE EXAMPLE 25	△	1
EXAMPLE 48	○	2	COMPARATIVE EXAMPLE 26	△	1
EXAMPLE 49	○	2			
EXAMPLE 50	○	2			

○: Particle retaining its shape △: Particle dissolved to some extent ×: Particle dissolved into a plate shape
 2: Particle retaining its original shape 1: Particle deformed 0: Particle no longer retaining its particular shape
 F: Particle dissolved before it was synthesized

(Evaluation test 5)

[0269] A 5% by weight particle solution was prepared by dissolving 0.5g of the particles prepared in each of EXAMPLES 1 to 50 and COMPARATIVE EXAMPLES 1 to 26 in 9.5g of a water/methanol (3/7) solution. Then, a small quantity of the solution was spread on slide glass (Coming's) coated with a silane coupling agent containing amino group, and thermally treated for 30 minutes in a drier kept at 150°C. Next, the coated slide glass was immersed in a THF bath (5L) for 20 minutes, and then naturally dried to observe the slide glass surface conditions. The slide glass having deposits on the surface was analyzed by an SEM to confirm the particle shape again. The evaluation results are given in Table 13.

[Table 13]

Test 2	Visually observed deposits	SEM analysis	Test 2	Visually observed deposits	SEM analysis
EXAMPLE 1	○	Particle retaining its original shape	EXAMPLE 39	○	Particle retaining its original shape
EXAMPLE 2	○	Particle retaining its original shape	EXAMPLE 40	○	Particle retaining its original shape
EXAMPLE 3	○	Particle retaining its original shape	EXAMPLE 41	○	Particle retaining its original shape

EP 1 344 795 A2

[Table 13] (continued)

Test 2	Visually observed deposits	SEM analysis	Test 2	Visually observed deposits	SEM analysis
EXAMPLE 4	○	Particle retaining its original shape	EXAMPLE 42	○	Spherical particle
EXAMPLE 5	○	Particle retaining its original shape	EXAMPLE 43	○	Spherical particle
EXAMPLE 6	○	Particle retaining its original shape	EXAMPLE 44	○	Spherical particle
EXAMPLE 7	○	Particle retaining its original shape	EXAMPLE 45	○	Spherical particle
EXAMPLE 8	○	Particle retaining its original shape	EXAMPLE 46	○	Spherical particle
EXAMPLE 9	○	Particle retaining its original shape	EXAMPLE 47	○	Spherical particle
EXAMPLE 10	○	Particle retaining its original shape	EXAMPLE 48	○	Spherical particle
EXAMPLE 11	○	Particle retaining its original shape	EXAMPLE 49	○	Spherical particle
EXAMPLE 12	○	Particle retaining its original shape	EXAMPLE 50	○	Spherical particle
EXAMPLE 13	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 1	×	-
EXAMPLE 14	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 2	×	-
EXAMPLE 15	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 3	×	-
EXAMPLE 16	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 4	×	-
EXAMPLE 17	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 5	×	-
EXAMPLE 18	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 8	×	-

[Table 13] (continued)

Test 2	Visually observed deposits	SEM analysis	Test 2	Visually observed deposits	SEM analysis
EXAMPLE 19	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 7	×	-
EXAMPLE 20	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 8	×	-
EXAMPLE 21	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 9	F	
EXAMPLE 22	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 10	F	
EXAMPLE 23	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 11	F	
EXAMPLE 24	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 12	F	
EXAMPLE 25	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 13	F	
EXAMPLE 26	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 14	F	
EXAMPLE 27	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 15	○	Deformed particle
EXAMPLE 28	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 16	○	Deformed particle
EXAMPLE 29	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 17	○	Deformed particle
EXAMPLE 30	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 18	○	Deformed particle
EXAMPLE 31	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 19	○	Deformed particle
EXAMPLE 32	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 20	×	-
EXAMPLE 33	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 21	×	-

[Table 13] (continued)

Test 2	Visually observed deposits	SEM analysis	Test 2	Visually observed deposits	SEM analysis
EXAMPLE 34	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 22	×	-
EXAMPLE 35	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 23	×	-
EXAMPLE 36	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 24	F	
EXAMPLE 37	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 25	○	Deformed particle
EXAMPLE 38	○	Particle retaining its original shape	COMPARATIVE EXAMPLE 26	○	Deformed particle
○: Deposits observed ×: No deposits observed (particle dissolved) F: Particle dissolved before it was synthesized					

[0270] It is apparent from the results of EXAMPLES and COMPARATIVE EXAMPLES (given in Tables 1 to 13) that the particles prepared in each of EXAMPLES 1 to 50 show improved resistance to heat and solvents as the crosslinked particles, and excellent glueability and adhesion as the reactive particles.

[0271] On the other hand, the particles prepared in each of COMPARATIVE EXAMPLES 1 to 19 show little effects of resistance to heat and solvents as the crosslinked particles, and those prepared in each of COMPARATIVE EXAMPLES 20 to 26 show little effects of glueability and adhesion as the reactive particles.

[0272] It is apparent, based on these results, that the novel carbodiimide-containing resin particles of the present invention have excellent effects of resistance to heat and solvents, and glueability and adhesion.

Advantage of the Invention

[0273] The hardening type reactive particles of the present invention are each comprising a base particle (A) of thermoplastic resin having a functional group and carbodiimide compound (B) impregnated only in the surface layer section or both surface layer section and inside of the base particle, wherein the base particle (A) and carbodiimide compound (B) are strong bonded to each other by the crosslinking reaction taking place under heating between the functional group in the former and carbodiimide group in the latter. As such, they show excellent performances in resistance to heat and solvents, and glueability and adhesion.

[0274] The hardening type reactive particles, keeping the above performances and being reactive crosslinked particles, can go into various areas, e.g., crosslinking agent, stabilizer for improving hydrolysis resistance, hardening agent for thermoplastic resins, adhesive agent, coating agent, paint, reinforcing material and aid for automobile and electric/electronic industries, furniture and building materials, and spacers for liquid crystals.

Claims

1. Hardening type reactive particles each comprising a base particle (A) of thermoplastic resin having a functional group and carbodiimide compound (B) impregnated only in the surface layer section or both surface layer section and inside of the base particle, wherein
the base particle (A) and carbodiimide compound (B) are strong bonded to each other by the crosslinking reaction taking place under heating between the functional group in the former and carbodiimide group in the latter.
2. The hardening type reactive particles according to Claim 1, wherein said base particle (A) has an average diameter

of 0.01 to 10,000 μ m.

3. The hardening type reactive particles according to Claim 1, wherein said base particle (A) is morphologically truly or nearly spherical.
4. The hardening type reactive particles according to Claim 1, wherein said functional group is at least one type of active hydrogen group selected from the group consisting of hydroxyl, carboxyl, amino and thiol group.
5. The hardening type reactive particles according to Claim 1, wherein said thermoplastic resin has 30 to 700 equivalents of said functional groups.
6. The hardening type reactive particles according to Claim 1, wherein said thermoplastic resin is one of styrene-based polymer, (meth)acrylate-based polymer, a copolymer produced by addition polymerization with another vinyl-based polymer, polymer produced by hydrogen transfer polymerization, polymer produced by polycondensation and polymer produced by addition condensation.
7. The hardening type reactive particles according to Claim 1, wherein said carbodiimide compound (B) is the carbodiimide resin represented by the chemical formula (1):



(wherein, R^1 and R^3 are each hydrogen or an organic residue of 1 to 40 carbon atoms, which is a compound having a functional group reactive with isocyanate group left by the functional group, and may be the same or different; R^2 is an organic residue which is a diisocyanate left by isocyanate group, where the diisocyanates may be different; Y is a bond formed by isocyanate group and a functional group reactive with isocyanate group; "n" is an integer of 1 to 100, representing average degree of polymerization; and each of R^1-Y and $Y-R^3$ may be isocyanate group halfway in the reaction to be converted into the carbodiimide).

8. The hardening type reactive particles according to Claim 7, wherein said carbodiimide resin has 50 to 500 equivalents of the carbodiimide (-NCN-) groups.
9. The hardening type reactive particles according to Claim 7, wherein said carbodiimide resin has an average molecular weight of 200 to 100,000.
10. The hardening type reactive particles according to Claim 7, wherein said carbodiimide resin has at least one type of hydrophilic segment and is soluble in water.
11. The hardening type reactive particles according to Claim 10, wherein said hydrophilic segment is represented by the chemical formula (1) with R^1 and R^3 being each at least one type of residue represented by one of the chemical formulae (2) to (5):

(i) a residue of alkyl sulfonate having at least one reactive hydroxyl group, represented by:



(wherein, R^4 is an alkylene group of 1 to 10 carbon atoms; and R^5 is an alkali metal),

(ii) a quaternary salt of a dialkylaminoalcohol residue represented by:




(wherein, R^6 is a lower alkyl group of 1 to 4 carbon atoms; R^7 is an alkylene or oxyalkylene group of 1 to 10 carbon atoms; and R^1 is a group derived from an agent for producing a quaternary salt),

(iii) a quaternary salt of a dialkylaminoalkylamine residue represented by:



(wherein, R^6 , R^7 and R^1 are each the same as the corresponding one in the formula (3)), and
 (iv) a poly(alkylene oxide) residue sealed with alkoxy group at the terminals, having at least one reactive hydroxyl group, represented by:



(wherein, R^8 is a lower alkyl group of 1 to 4 carbon atoms; R^9 is hydrogen atom or methyl group; and "m" is an integer of 2 to 30).

12. A process for producing the hardening type reactive particles of one of Claims 1 to 11 comprising two steps: the first step in which the base particle (A) of thermoplastic resin having a functional group is mixed with the carbodiimide compound (B) in the presence of at least one type of solvent which dissolves (B) but not (A), selected from the group consisting of water and organic solvents, to have the latter impregnated only in the surface layer section or both surface layer section and inside of the former; and the subsequent second step in which the above mixture is thermally treated.
13. The process for producing the hardening type reactive particles according to Claim 12, wherein said base particle (A) is morphologically truly or nearly spherical.
14. The process for producing the hardening type reactive particles according to Claim 13, wherein said base particle (A) is the one prepared beforehand by suspension, emulsion, dispersion or seed polymerization.
15. The process for producing the hardening type reactive particles according to Claim 12, wherein said base particle (A) is immersed in a solution of the carbodiimide compound (B) dissolved in at least one type of solvent selected from the group consisting of water and organic solvents in said first step.
16. The process for producing the hardening type reactive particles according to Claim 15, wherein concentration of said carbodiimide compound (B) in said solution is 5 to 60% by weight, determined by the following formula:

$$\text{Solution concentration (\% by weight)} = 100 \times (\text{whole solution-solvent}) / \text{whole solution.}$$

17. The process for producing the hardening type reactive particles according to Claim 12, wherein said solvent is water, a mixture of water and a lower alcohol, or toluene.
18. The process for producing the hardening type reactive particles according to Claim 12, wherein said base particle (A) is mixed with said carbodiimide compound (B) in a ratio of 0.1 to 20 equivalents of the carbodiimide group in said carbodiimide compound (B) to equivalent of the functional group in said base particle (A).
19. The process for producing the hardening type reactive particles according to Claim 12, wherein said thermal treatment in the second step is effected at 10 to 200°C.
20. The process for producing the hardening type reactive particles according to Claim 12, wherein said thermal treatment in the second step is effected for 1 to 24 hours.
21. The process for producing the hardening type reactive particles according to Claim 12, wherein said functional group is at least one type of active hydrogen group selected from the group consisting of hydroxyl, carboxyl, amino and thiol group.
22. The process for producing the hardening type reactive particles according to Claim 21, wherein said thermoplastic resin is one of styrene-based polymer, (meth)acrylate-based polymer, a copolymer produced by addition polym-

erization with another vinyl-based polymer, polymer produced by hydrogen transfer polymerization, polymer produced by polycondensation or polymer produced by addition condensation.

23. The process for producing the hardening type reactive particles according to Claim 12, wherein said carbodiimide compound (B) has an average molecular weight of 200 to 100,000.
24. The process for producing the hardening type reactive particles according to Claim 12, wherein said carbodiimide compound (B) has at least one type of hydrophilic segment and is soluble in water.
25. The process for producing the hardening type reactive particles according to Claim 24, wherein said hydrophilic segment is represented by the chemical formula (1) with R¹ and R³ being each at least one type of residue represented by one of the chemical formulae (2) to (5).
26. The process for producing the hardening type reactive particles according to Claim 12, wherein at least one type of additive selected from the group consisting of dispersant, antioxidant, stabilizer and emulsifier is added to said first step, in addition to the base particle (A) and carbodiimide compound (B).
27. A crosslinking agent which comprises the hardening type reactive particles according to one of Claims 1 to 11.
28. A stabilizer for improving hydrolysis resistance which comprises the hardening type reactive particles according to one of Claims 1 to 11.
29. A thermoplastic resin-hardening agent which comprises the hardening type reactive particles according to one of Claims 1 to 11.
30. An adhesive agent which comprises the hardening type reactive particles according to one of Claims 1 to 11.
31. A coating material or paint which comprises the hardening type reactive particles according to one of Claims 1 to 11.
32. A reinforcing material for the electric/electronic areas which comprises the hardening type reactive particles according to one of Claims 1 to 11.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 344 795 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
02.06.2004 Bulletin 2004/23

(51) Int Cl.7: C08K 9/04, C08K 9/08,
C08J 3/24

(43) Date of publication A2:
17.09.2003 Bulletin 2003/38

(21) Application number: 03100546.5

(22) Date of filing: 05.03.2003

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR
Designated Extension States:
AL LT LV MK

(30) Priority: 13.03.2002 JP 2002068151

(71) Applicant: NISSHINBO INDUSTRIES, INC.
Tokyo 103 (JP)

(72) Inventors:

- Ikuo, Takahashi Nisshinbo Ind. INC.
Midori-ku, Chiba-shi Chiba, Chiba (JP)
- Toshifumi, Hashiba Nisshinbo Ind. INC.
Midori-ku, Chiba-shi Chiba, Chiba (JP)
- Kazutoshi, Hayakawa Nisshinbo Ind. INC.
Midori-ku, Chiba-shi Chiba, Chiba (JP)

(74) Representative: Moinas, Michel et al
Cabinet Michel Moinas
13 Chemin du Levant
01210 Ferney-Voltaire (FR)

(54) Carbodiimide-containing hardening type reactive particles, process for producing the same, and use of the same

(57) A hardening type reactive particles which contain a carbodiimide compound in such a way to have the reactive performance the carbodiimide group inherently has only in the surface layer section or both surface layer section and inside of the base particle, without deforming shape of the base particle. The hardening type reactive particles each comprising a base particle (A) of thermoplastic resin having a functional group and carbodiimide compound (B) impregnated only in the sur-

face layer section or both surface layer section and inside of the base particle, wherein the base particle (A) and carbodiimide compound (B) are strong bonded to each other by the crosslinking reaction taking place under heating between the functional group in the former and carbodiimide group in the latter, and a process for producing the same.

EP 1 344 795 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 10 0546

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IntCl.7)
D,X	DATABASE CHEMABS [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; OKUTANI, HARUO OKUTANI, HARUO: "Electrophotographic toner containing polyolefin crosslinked with carbodiimide Electrophotographic toner containing polyolefin crosslinked with carbodiimide" retrieved from STN Database accession no. 2000:378193 XP002275263 * abstract * & JP 2000 155441 A (TOMOEGAWA PAPER CO., LTD., JAPAN TOMOEGAWA PAPER CO., LTD., JAPAN) 6 June 2000 (2000-06-06) ---	1-32	C08K9/04 C08K9/08 C08J3/24
X	DATABASE CHEMABS [Online] CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; TSUJI, TAKASHI ET AL TSUJI, TAKASHI ET AL: "Dispersible latex particles, their preparation and use for biochemical immobilization Dispersible latex particles, their preparation and use for biochemical immobilization" retrieved from STN Database accession no. 1989:208511 XP002275264 * abstract * & JP 63 116695 A (NITTO ELECTRIC INDUSTRIAL CO., LTD., JAPAN NITTO ELECTRIC INDUSTRIAL C) 20 May 1988 (1988-05-20) ---	1-7, 12-22, 27-32	TECHNICAL FIELDS SEARCHED (IntCl.7) C08K C08J
A	EP 0 878 496 A (NISSHIN SPINNING) 18 November 1998 (1998-11-18) * the whole document * --- -/--	1-32	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 29 March 2004	Examiner Dury, O
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 (03.02) (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 10 0546

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (InCL.7)
A	PATENT ABSTRACTS OF JAPAN vol. 0177, no. 04 (C-1146), 22 December 1993 (1993-12-22) & JP 05 239223 A (NISSHINBO IND INC), 17 September 1993 (1993-09-17) * abstract * -----	1-32	
			TECHNICAL FIELDS SEARCHED (InCL.7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 29 March 2004	Examiner Dury, O
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1502 03.82 (PO4C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 10 0546

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

29-03-2004

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 2000155441	A	06-06-2000	NONE	
JP 63116695	A	20-05-1988	JP 1982351 C	25-10-1995
			JP 7004243 B	25-01-1995
EP 0878496	A	18-11-1998	JP 10316930 A	02-12-1998
			EP 0878496 A1	18-11-1998
			US 6124398 A	26-09-2000
JP 05239223	A	17-09-1993	JP 3172887 B2	04-06-2001